

Standard Recommended Practice

Corrosion Control of Steel Fixed Offshore Structures Associated with Petroleum Production

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE International standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protecting anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE International assumes no responsibility for only those official NACE International interpretations issued by NACE International in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE International standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE International standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE International standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE International standards are subject to periodic review, and may be revised or withdrawn at any time without prior notice. NACE International requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication. The user is cautioned to obtain the latest edition. Purchasers of NACE International standards may receive current information on all standards and other NACE International publications by contacting the NACE International Membership Services Department, 1440 South Creek Dr., Houston, Texas 77084-4906 (telephone +1 281/228-6200).

Revised 2003-06-21 Revised March 1994 Revised May 1983 Approved April 1976 NACE International 1440 South Creek Drive Houston, Texas 77084-4906 +1 281/228-6200

ISBN 1-57590-170-6 ©2003, NACE International

Foreword

Offshore structures represent large capital investments. Structures are being placed in offshore areas worldwide and are being designed to withstand forces resulting from hurricanes, arctic storms, tidal currents, earthquakes, and ice floes. Moreover, platform structures are currently being placed in deeper waters and, therefore, have become larger, more complex, and more expensive. Control of corrosion on structures is necessary for the economic development of oil and gas production, to provide safe support for working and living areas, and to avoid potential harm to the environment. For the purposes of this standard, offshore structures are considered to be stationary structures (platforms or subsea facilities) that are fixed to the sea floor by gravity, piling, and/or mooring cables.

This NACE International standard is intended for use by corrosion control personnel concerned with the corrosion of steel fixed offshore platforms associated with petroleum production. It outlines materials, practices, and methods for control of corrosion for steel fixed structures associated with petroleum production located in offshore areas. The purpose is to facilitate more effective corrosion protection of structures by the presentation of reliable information. Corrosion on offshore structures can be divided into three major areas: the submerged zone, the splash zone, and the atmospheric zone. The submerged zone also includes that portion of the structure below the mudline. This standard does not include procedures for the control of internal corrosion of wells, piping, and associated equipment that may be in use on the structure, but does include external protection of these items in the atmospheric zone on the structure.

This standard was originally issued in 1976 and revised in 1983 by Task Group (TG) T-1-2 on North Sea Corrosion Problems. It was revised in 1994 by Task Group T-1-5 and in 2003 by Task Group 170, which is administered by Specific Technology Group (STG) 30 on Oil and Gas Production—Cathodic Protection. TG 170 is sponsored by STGs 02 on Protective Coatings and Linings—Atmospheric and STG 05 on Cathodic/Anodic Protection. It is issued by NACE International under the auspices of STG 30.

In NACE standards, the terms *shall, must, should,* and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual,* 4th ed., Paragraph 7.4.1.9. *Shall* and *must* are used to state mandatory requirements. The term *should* is used to state something good and is recommended but is not mandatory. The term *may* is used to state something considered optional.

NACE International Standard Recommended Practice

Corrosion Control of Steel Fixed Offshore Structures Associated with Petroleum Production

Contents

1.General	1
2.Definitions	1
3.Structural Design for Corrosion Control	3
4. Criteria for Cathodic Protection	6
5.Design of Cathodic Protection Systems	9
6.Installation of Cathodic Protection Systems	16
7.Control of Interference Currents	17
8.Dielectric Shields	18
9. Operation and Maintenance of Cathodic Protection Systems	19
10. Splash Zone Corrosion Control Measures	20
11. Maintenance of Splash Zone Corrosion Control Measures	22
12. Surface Preparation	23
13. Coatings	25
14. Coatings Inspection	29
15. Corrosion Control Records	30
References	32
Bibliography	33
Appendix A—Typical Design Parameters for Offshore Petroleum Production	35
Appendix B-Energy Capabilities and Consumption Rates of Various Comme	rcial
Galvanic Anodes Available for Cathodic Protection of Offshore Structures	37
Appendix C—Consumption Rates in Seawater of Various Commercial Types	s of
Impressed Current Anodes Available for Cathodic Protection of Offshore Structure	s 38
Appendix D-Typical Method for Calculation of Galvanic Anode Current Output U	sing
Initial, Maintenance, and Final Current Densities	39
Appendix E-Typical Method of Calcuation of Galvanic Anode Current Output U	sing
Design Slope and Maintenance Current Density	41
Table A1—Design Criteria for Cathodic Protection Systems	36
Table B1—Energy Capabilities and Consumption Rates of Galvanic Anode Materia	ls in
Seawater	38
Table C1—Consumption Rates of Impressed Current Anode Materials	39
Figure A1—Current Density/Temperature Curves	37

Section 1: General

1.1 This standard provides guidelines for establishing minimum requirements for the control of corrosion on steel fixed offshore structures associated with petroleum production, and on the external portions of associated oil and gas handling equipment. Fixed structures include platforms, tension leg platforms (TLPs), and subsea templates. This standard does not include guidelines for corrosion control of temporarily moored mobile vessels used in petroleum production.

1.2 For this standard, corrosion on structures is divided into three zones: the submerged, splash, and atmospheric zones. Each zone is examined separately.

1.3 This standard does not designate guidelines for every specific situation because of the complexity of environmental conditions. In many instances, there may be several solutions to the problem and, when appropriate, meritorious alternative solutions have been included.

1.4 This standard does not include guidelines for corrosion control of the internal portions of wells, piping, and associated equipment that may be installed on or attached to structures.

1.5 This standard includes corrosion control of the external surfaces of attached pipelines above the splash zone. When ownership of the pipeline is different from that of the structure, the structure owner's responsibility for the pipeline usually ends at a designated point or valve on the structure.

1.6 Underwater pipelines and pipeline risers are specifically excluded from this standard.

1.7 Alternative methods are acceptable to accomplish the objectives of this standard; however, deviation should be made only if, in the opinion of a competent corrosion specialist, the objectives expressed in the standard have been achieved.

Section 2: Definitions

NOTE: Additional definitions for cathodic protection and coatings technology may be found in NACE Standard RP0169,¹ the *NACE Corrosion Engineer's Handbook*,² and the NACE International 2002 *Glossary of Corrosion-Related Terms*.³

Anchor Pattern: The irregular peak and valley pattern created on the surface of steel by the effect of blasting media hitting the steel at high velocity.

Anode: The electrode of an electrochemical cell at which oxidation occurs. Electrons flow away from the anode in the external circuit. Corrosion usually occurs and metal ions enter the solution at the anode.

Atmospheric Zone: The zone of the structure that extends upward from the splash zone and is exposed to sun, wind, spray, and rain.

Calcareous Coating or Deposit: A layer consisting of calcium carbonate and other salts deposited on the surface. When the surface is cathodically polarized as in cathodic protection, this layer is the result of the increased pH adjacent to the protected surface.

Cathode: The electrode of an electrochemical cell at which reduction is the principal reaction. Electrons flow toward the cathode in the external circuit.

Cathodic Disbondment: The destruction of adhesion between a coating and the coated surface caused by products of a cathodic reaction. **Cathodic Protection**: A technique to reduce the corrosion of a metal surface by making that surface the cathode of an electrochemical cell.

Chalking: The development of loose, removable powder (pigment) at the surface of an organic coating, usually caused by weathering. Controlled chalking provides for self-cleaning of the surface and leaves the surface in good condition for recoating.

Chlorinated Rubber: A particular film former used as a binder, made by chlorinating rubber.

Corrosion: The deterioration of a material, usually a metal, that results from a reaction with its environment.

Corrosion Specialist: A person who, by reason of his/her education and/or experience, is qualified to evaluate and solve problems related to the corrosion of materials. In this standard, corrosion specialist refers to one who is qualified in the control of corrosion in marine environments.

Crosslink: The result of a chemical reaction linking two chains in the molecular structure of a coating and changing the final state of the coating.

Current: (1) A flow of electric charge. (2) The amount of electric charge flowing past a specified circuit point per unit time, measured in the direction of net transport of positive charges. (In a metallic conductor, this is the opposite direction of the electron flow.)

Current Density: The current to or from a unit area of an electrode surface.

Depolarization: The removal of factors resisting the current in an electrochemical cell.

Dielectric Shield: An electrically nonconductive material, such as a coating, sheet, or pipe, that is placed between an anode and an adjacent cathode, usually on the cathode, to improve current distribution in a cathodic protection system.

Doubler Plate: An additional plate or thickness of steel used to provide extra strength at the point of anode attachment to a structure.

Electrical Isolation: The condition of being electrically separated from other metallic structures or the environment.

Electrolyte: A chemical substance containing ions that migrate in an electric field.

Epoxy: Type of resin formed by the reaction of aliphatic or aromatic polyols (like bisphenol) with epichlorohydrin and characterized by the presence of reactive oxirane end groups.

Faying: Especially close fitting. The term originally described the fit between hull timbers in wooden ships.

Foreign Structure: Any metallic structure that is not intended as a part of a system under cathodic protection.

Galvanic Anode: A metal that provides sacrificial protection to another metal that is more noble when electrically coupled in an electrolyte. This type of anode is the electron source in one type of cathodic protection.

Holiday: A discontinuity in a protective coating that exposes unprotected surface to the environment.

Impressed Current: An electric current supplied by a device employing a power source that is external to the electrode system. (An example is direct current for cathodic protection.)

Interference Current (Stray Current): Current through paths other than the intended circuit. For the purposes of this standard, interference current is current discharged to the electrolyte from a structure that may be either (1) not an intended part of the circuit or (2) an intended part of the circuit that is not adequately connected to the current source.

Inorganic Zinc-Rich Coating (Paint): Coating containing a metallic zinc pigment (typically 75 wt% zinc or more in the dry film) in an inorganic vehicle.

"J" Tube: A curved tubular conduit designed and installed on a structure to support and guide one or more pipeline risers or cables. **Mill Scale**: The oxide layer formed during hot fabrication or heat treatment of metals.

Mudline: The ocean floor at the location of interest.

Padeye: A lifting or connection point that is shaped like an eye and is used to accommodate hooks, tackle, or slings.

Pipeline: A conduit for carrying produced oil, water, and gas between structures or between structures and onshore processing facilities.

Platform: An offshore structure used to accommodate oil and/or gas wells, related production equipment, pipelines, and/or living quarters.

Polarization: The change from the open-circuit potential as a result of current across the electrode/electrolyte interface.

Polymerization: The process of uniting a number of small chemical units to form a larger one. The product of such a union is called a *polymer*.

Primer: A coating material intended to be applied as the first coat on an uncoated surface. The coating is specifically formulated to adhere to and protect the surface as well as to produce a suitable surface for subsequent coats. (Also referred to as *Prime Coat*.)

Reference Electrode: An electrode whose open-circuit potential is constant under similar conditions of measurement, which is used for measuring the relative potentials of other electrodes.

Resin: Generally refers to a class within the broad family of plastics or polymers and usually indicates stability for use as a binder for coating materials. The term resin is usually modified by other words to denote type, for example: alkyd resin, vinyl resin, ester resin, or epoxy resin.

Riser: (1) That section of pipeline extending from the ocean floor up to an offshore structure. (2) The vertical tube in a steam generator convection bank that circulates water and steam upward.

Silver/Silver Chloride Electrode: For the purposes of this standard, a reference electrode that uses seawater as the junction electrolyte, for example, the Ag/AgCl/seawater electrode.

Splash Zone: The zone of the structure that is alternately in and out of the water because of the influence of tides, winds, and seas. Excluded from this zone are surfaces that are wetted only during major storms.

Structure: Stationary structure (platform or subsea facility) that is fixed to the sea floor by gravity, piling, and/or mooring cables.

Structure-to-Electrolyte Potential: The potential difference between the surface of a buried or submerged metallic structure and the electrolyte that is measured with reference to an electrode in contact with the electrolyte.

Submerged Zone: The zone that extends downward from the splash zone and includes that portion of the structure below the mudline.

Subsea Template: A structure intended to be placed on the sea floor to accommodate oil and/or gas wells, related production equipment, and/or pipelines.

Thinner: A volatile solvent used to lower the viscosity of a coating material.

Thermoplastic: A material capable of being repeatedly softened by heat and hardened by cooling.

Thermosetting: A material that undergoes a chemical reaction from the action of heat and pressure, catalysts, and ultraviolet light, leading to a relatively infusible state.

Tie Coat: A special-purpose intermediate coat, usually organic, used to act as a bridge between a primer and finish coat to overcome either incompatibility or application problems between the primer and finish coats. **Urethane**: A chemically cured coating consisting of a solution vinyl, vinyl acrylic, or acrylic base reacted with isocyanate converter to form a tough, durable, glossy coating.

Valve Reach Rod: A long valve stem extension that enables personnel on the surface to open and close a ballast control valve located near the bottom of the structure.

Vinyl Acrylic: Vinyl resin modified with acrylic resin in solvent solution.

Vinyl Coatings: Vinyl resin dissolved in a solvent. Vinyl solution coatings may be air dried or baked.

Voltage: An electromotive force, or a difference in electrode potentials, expressed in volts or millivolts.

Voltage Drop: The voltage across a current-carrying resistance in accordance with Ohm's Law.

Wash Primer: A thin, inhibiting primer, usually chromate pigmented, with a polyvinyl butyral binder.

Wear Plate: A sacrificial member attached to the structure in the splash zone to protect it from anticipated corrosion and/or erosion caused by ice and/or high-velocity, silt-laden water.

Section 3: Structural Design for Corrosion Control

3.1 Introduction

3.1.1 This section recommends design features that simplify corrosion control of structural steel in the atmospheric, splash, and submerged zones of offshore structures. The structural design parameters that must be considered for an offshore structure to resist dynamic and static loads are the responsibility of civil and structural engineers and are not a part of this standard.

3.2 Splash Zone

3.2.1 This is the zone of an offshore structure that is alternately in and out of the water because of the influence of tides, winds, and seas. Excluded from this zone are surfaces that are wetted only during major storms. In the Gulf of Mexico, the splash zone typically covers an interval of about 2 m (6 ft); in Cook Inlet, Alaska, the interval approaches 9 m (30 ft); during winter storms the splash zone in the North Sea can be 10 m (33 ft).

3.2.2 A structure should be designed to minimize the surface area of steel in the splash zone. Intersecting "T," "K," and "Y" joints should be avoided in the splash zone.

3.2.3 Methods for controlling corrosion in the splash zone are presented in Section 10.

3.2.4 Added metal thickness, either as a weld-applied wrap or as a heavier-wall tubular member, may be used to compensate for anticipated splash zone corrosion over the life of an offshore structure.

In determining the required level of added wall thickness the following factors should be taken into account:

- Required life of the structure
- Use of lifetime minimum or no maintenance coatings (e.g., thermal-sprayed aluminum)
- Maintenance philosophy if there is coating damage (how long is it likely to be left to corrode before the coating is repaired)
- Corrosion rate of carbon steel in seawater at the location the structure will be installed

3.2.5 Piping, etc., passing through the splash zone, that is to be removed after installation, should preferably be clamped to the structural member, not welded to it.

3.3 Atmospheric Zone

3.3.1 This zone of an offshore structure extends upward from the splash zone. It is exposed to sun, wind, spray, and rain.

3.3.2 Corrosion in this zone is typically controlled by the application of a protective coating system (see Section 12). Steel surface areas requiring coating should be minimized and/or made accessible by:

3.3.2.1 Substituting tubular members for other structural shapes.

3.3.2.2 Seal welding and "boxing in" structural units.

3.3.2.3 Eliminating skip welding.

3.3.2.4 Eliminating close-fitting and faying surfaces.

3.3.2.5 Providing padeyes to make scaffolding and maintenance painting easier.

3.3.3 Nonferrous and nonmetallic materials minimize atmospheric corrosion problems. For example, quarters modules and lifeboats are available in aluminum and composite materials such as glass-reinforced polyester (GRP). Corrosion-resistant materials and composites can be used for handrails, electrical conduit, stair treads, and deckplates. When dissimilar metals are used, care must be taken to prevent galvanic corrosion of the active component. Composite materials such as GRP may be substituted for metals when resistance to corrosion and/or weight reduction is desired. Safety aspects regarding the use of these materials should be considered.

3.3.4 Drilling fluids can damage protective coating systems and nonferrous metals such as aluminum and zinc. Solid decks, splash walls, and a good drainage system minimize coating damage and pollution caused by drilling fluids.

3.4 Submerged Zone—External Areas

3.4.1 This zone extends downward from the splash zone and includes any portion of the structure below the mudline. Corrosion control for the external areas of the submerged zone should be achieved through the application of cathodic protection (CP) or by CP in conjunction with coatings. To simplify the application of effective cathodic protection, the following design features are recommended:

3.4.1.1 Tubular members should be used wherever possible. Recessed corners in channels and "I" beams are difficult to protect. The crevice formed by placing angles or channels back-toback cannot be reliably protected, and such construction should not be used.

3.4.1.2 For structures in which fatigue or corrosion fatigue is a critical factor, welds may be stress relieved to reduce the likelihood of fatigue or corrosion fatigue failures in the heat-affected zone (HAZ). This may be important in cold-water environments, where polarization tends to develop slowly, or in partially shielded areas on a structure. See API⁽¹⁾ RP 2A-WSD⁴ and RP 2A-LRFD.⁵

3.4.1.3 All weld joints should be continuous. Skip and tack welding should not be used. If lap joints are used, both edges should be continuously welded. Bolted and riveted fittings should be avoided.

3.4.1.4 Ballast control valve reach rods should be designed so that they can be removed after a structure has been set, whenever practical. If left in place, they may shield adjacent structural members from the CP current. Loose reach rods can also cause chafing damage to the structure.

3.4.1.5 Piping, such as grout lines, well cutting lines, discharge lines, water supply casings, and pipeline risers, if clustered around a large structural member, can cause shielding and interfere with the flow of CP current. Piping not needed for continued operations should be removed if economically feasible. Lines not cheduled for removal should be located to avoid CP shielding. A minimum clear spacing of 1.5 diameters of the smaller pipe should be provided. Coatings may be used to minimize CP shielding.

3.4.1.6 Supplemental or replacement impressed current anodes are sometimes required after a structure has been placed in service. Designers should consider providing spare "J" tubes for pulling cables for add-on anodes and/or providing brackets, guides, or clamps to facilitate such anode additions or replacement.

3.4.1.7 Structure pilings should be protected by the structure CP system. Piles driven through jacket legs are normally bonded to the jacket by welding, and thus receive CP. Skirt piles are typically driven inside submerged piling grout tubes and then are grouted in place. Skirt piles may be electrically connected to the jacket by means of guide shoes, centralizers, or other acceptable bonding methods. Corrosion rates below the mudline are considered to be low. However, mudline corrosion can be significant for structures with long lifetimes. All mudline members, critical to the integrity of the offshore structure, should be properly connected to the CP system.

⁽¹⁾American Petroleum Institute (API), 1220 L St. NW, Washington, DC 20005.

3.4.1.8 Well-casing conductors must be electrically connected to the structure when the well-casing conductors are considered necessary to the integrity of the well casings.

3.4.1.9 All steel to be protected must have electrical continuity with the CP system (preferably by welded contact). This electrical continuity should be capable of lasting for the lifetime of the structure.

3.5 Submerged Zone—Internal Areas

3.5.1 Corrosion normally is negligible on the internal surfaces of structural members or in compartments that are sealed and have no contact with either the atmosphere or the seawater. Whenever possible, the design should provide for sealed compartments.

3.5.2 During offshore structure launching and tilt-up operations, some structural members are flooded and remain flooded for the life of the structure. To prevent internal corrosion, the flooding valves should be closed after flooding, to isolate the flooded chambers from contact with atmospheric oxygen. In compartments in which circulation of seawater is possible, provisions should be made to curtail internal corrosion. CP or a combination of CP and coatings should be used. Tanks and compartments with a gas phase should be coated internally where condensation may occur and CP is not effective. The use of impressed current systems in these compartments should be avoided due to development of toxic and corrosive chlorine gas by the anode.

3.5.2.1 Piping, valves, submerged pumps, and other special equipment must also be protected; particularly when different metallic materials are used there is high risk of galvanic corrosion. This is important, for example, when corrosion-resistant alloy piping is routed through structural steel bulkheads.

3.5.3 In flooded compartments with a source of organic nutrients, bacterial growth may generate organic acids, carbon dioxide, and/or hydrogen sulfide (H_2S) that can cause corrosion. Bacteria-related corrosion can be controlled by the use of internal CP, coatings, and/or microbiocides. **Caution**: H_2S is toxic, even at low concentrations.

3.5.4 Pipelines are sometimes installed in pull tubes, or "J" tubes. To restrict contact with seawater and atmospheric oxygen, the pull-tube annulus should be sealed at the above-water end with a suitable nonwick-

ing packing after the lines have been pulled into position.

3.5.5 Floating production units have mooring systems intended for long-term service. Special considerations are required for the corrosion protection of these mooring lines.

3.5.5.1 Chains: Chains are protected by corrosion allowance. Corrosion allowance is added on the diameter of the chain (bar), such that twice the corrosion rate at the location must be used when calculating the additional material. In the splash zone a higher corrosion allowance is required. Depending on chain handling, the wear could be substantial. Many permanent floating production units require minimal handling of the mooring systems. Instead of full corrosion allowance in the splash zone, the splash zone chain segment can be "turned" once during the lifetime; thus the submerged part becomes the splash zone part and vice versa after half the intended design life.

Experience has shown that CP on the structure is effective approximately 30 to 60 m (100 to 200 ft) out from the structure. The distance depends on the connection of the chain to the structure, the size of the chain, and the line tension. This CP should not be included in the mooring line design, but additional CP must be applied to prevent underprotection of the steel fairleads and steel structure.

3.5.5.2 Wire ropes: Wire ropes are normally made from galvanized wires and have an outer extruded corrosion protection jacket from polyure-thane, polyethylene, or a similar material. In addition, grease is injected to prevent water from penetrating into the rope and ease movement between the individual wires. Sacrificial zinc wires may be included. Because steel wires have very high strength, hydrogen effects should be evaluated as part of any CP of the ropes.

It is important that the external jacket completely cover the connection of the wire rope to the socket end and prevent water from penetrating into the wire rope.

3.5.5.3 For mooring lines and anchors, bacterial corrosion in the parts exposed to bottom sediments must be evaluated and, if necessary, protection measures taken in the form of CP, coating, or corrosion allowance.

Section 4: Criteria for Cathodic Protection

4.1 Introduction

4.1.1 This section lists criteria and related inspection methods for CP. Compliance with the criteria either separately or collectively indicates whether the structure is protected.

4.2 General

4.2.1 The objective of using CP is to control the corrosion of metallic surfaces in contact with electrolytes.

4.2.2 The criteria in Paragraph 4.3 have been developed through laboratory experiment or field experience. Structure protection need not be limited to these criteria if it can be demonstrated by other means that control of corrosion has been achieved.

4.2.3 The selection of a particular criterion for achieving the objective in Paragraph 4.2.1 depends, in part, on past experience with similar structures and environments in which the criterion has been used successfully.

4.2.4 No single criterion for evaluating the effectiveness of CP has proved to be satisfactory for all conditions. A combination of criteria may be needed for a single structure.

4.3 Criteria

4.3.1 Potential measurements

4.3.1.1 A negative (cathodic) voltage of at least -0.80 V measured between the structure surface and a silver/silver chloride (20 ohm-cm seawater) reference electrode (Ag/AgCl [sw]) contacting the water is necessary. Normally, this voltage should be measured with the protective current applied. This -0.80 V criterion includes the voltage drop across the steel/water interface, but does not include the voltage drop in the water (see Paragraphs 4.5.1.1 and 4.6.1).

4.3.1.2 As an alternative to the criterion in Paragraph 4.3.1.1, a minimum negative (cathodic) voltage shift of 300 mV is produced by the application of protective current. This voltage shift shall be measured between the structure surface and a reference electrode contacting the water; it includes the voltage drop across the steel/water interface, but does not include the voltage drop in the water (see Paragraphs 4.5.1.1 and 4.6.1). 4.3.1.3 The potential at which corrosion is controlled is a function of the temperature and the environment. In waters exposed to the air and at typical ambient temperatures, the criteria listed in Paragraphs 4.3.1.1 and 4.3.1.2 have proved to be satisfactory. For other circumstances, the potential to control corrosion can be estimated using the Nernst equation.⁶

4.3.2 Visual inspection

4.3.2.1 Any visual inspection method (diver visual or feel, physical measurement, photography, or television) should indicate no progression of corrosion beyond limits acceptable for intended structure life throughout the structure.

4.3.3 Coupons

4.3.3.1 Corrosion type and rate must be within limits acceptable for intended structure life.

4.4 Alternative Reference Electrodes

4.4.1 Other standard reference electrodes that may be substituted for the Ag/AgCl (sw) are listed below with their voltage equivalent to -0.80 V referred to a Ag/AgCl (sw):

4.4.1.1 Saturated copper/copper sulfate reference electrode (CSE): -0.85 V (or more negative for protection). NOTE: This electrode is not stable for long-term immersion service.

4.4.1.2 High-purity zinc reference electrode: +0.25 V (or less positive for protection) corresponding to ASTM⁽²⁾ (B 418⁷ Type II, high-purity zinc having the following composition limits: aluminum: 0.005% maximum; cadmium: 0.003% maximum; iron: 0.0014% maximum; zinc: balance.

4.4.1.3 Saturated calomel reference electrode (SCE [saturated KCI]): -0.78 V (or more negative for protection).

4.4.1.4 MIL specification⁽³⁾ zinc reference electrode: +0.25 V (or less positive for protection) corresponding to MIL-A-18001⁸ having the following composition limits: aluminum: 0.10% to 0.50%; cadmium: 0.025% to 0.15%; iron: 0.005% maximum; lead: 0.005% maximum; copper: 0.005% maximum; silicon: 0.125% maximum.

⁽²⁾ASTM International, 100 Barr Harbor Drive, West Conshochocken, PA 19428.

⁽³⁾Military Specification, available from Government Printing Office, Washington, DC 20402.

4.4.1.5 Ag/AgCl (saturated KCl): -0.76 V (or more negative for protection).

4.5 Methods of Measuring and Evaluating CP

4.5.1 The most common method of evaluating the CP level is to measure electrical potential between the structure and a suitable reference electrode.

4.5.1.1 Potential measurements should be made with the reference electrode located in the water as close as practicable to the structure to minimize included voltage drops. Measurements taken with the electrode close to a structure member but distant from anodes and in areas of greatest shielding should be given major consideration in evaluating the protective level of a structure.

4.5.1.2 The most frequently used method of measuring potentials involves suspending the reference electrode freely in the water from a designnated location on the structure. The electrode is lowered to a specified series of depths for readings, and the process is repeated at other appropriate points on the structure. The location of the electrode may not be known because of drift resulting from water currents. This method is useful for determining the general condition of the CP system, but may not define problem areas on marginally protected structures.

4.5.1.3 The reference electrode may be carried by a diver or a remotely operated vehicle (ROV). This method provides excellent knowledge of electrode location and can result in a potential survey in any desired degree of detail. Diver safety must be considered during evaluation of impressed current protected structures. This may involve limiting the output from or de-energizing at least a part of the system for the duration of the measurements. If the system is de-energized, the effect of the reduction on the level of protection should be considered during the evaluation of the potential measurements.

4.5.1.4 The reference electrode may be run down a guide wire for better control of its location. The guide wire may be permanently installed on the structure, or it may be temporarily installed with the aid of a heavy weight to anchor it at the bottom. If temporarily installed, the wire (if metallic) should be electrically isolated from the structure. The guided electrode is capable of providing more accurate potential information than the freely suspended electrode, depending on the proximity of the guide wire to the members of the structure.

4.5.1.5 A number of permanent reference electrodes may be mounted on a structure. While the exact electrode locations are known, the information obtained from these electrodes is limited to the adjacent structure surfaces. Although this limitation holds true for any potential measurement, this method can provide a reproducible basis for comparing potentials at different times. The accuracy of permanent electrodes should be periodically checked against another electrode. Dual reference electrodes that combine zinc and silver-silver chloride references into a single installed permanent unit also help to detect/ reduce malfunctions.

4.5.1.6 In addition to reference electrodes, some structures have been equipped with permanent monitors to measure current density and current output from representative galvanic anodes. These devices are particularly useful when dealing with new structure designs, or new environments in which precise CP design criteria are not available. These devices typically use calibrated shunts to arrive at the current output or current density value; signals are usually transmitted top-side using hard-wired connections.

4.5.2 In addition to potential surveys, current density surveys can produce valuable data. Current density surveys utilize specially designed reference electrode arrays that measure the voltage gradient in the seawater around the structure. Although these surveys do not determine the level of protection present on the structure, they may be useful in determining current distribution and predicting remaining anode life.

4.5.3 Visual inspection is sometimes used to gain detailed knowledge not attainable by other means.

4.5.3.1 Divers may be employed to inspect visually or by feel if turbidity or light conditions so dictate.

4.5.3.2 Visual inspection using suitable instruments may include physical measurements such as the crack length and depth, wall thickness, or pit depth, as well as anode size and condition.

4.5.3.3 Underwater photography may be used to provide a permanent record of conditions.

4.5.3.4 Underwater television can provide a running topside view if decisions must be made while underwater work is in progress. Videotapes can provide a permanent record of the underwater conditions.

4.5.4 Steel coupons with metallurgy similar to that of the structure can be placed on a structure for later removal to determine the effectiveness of corrosion control measures. Coupons might be especially useful in areas suspected of being comparatively inaccessible to CP current.

RP0177-2003

4.6 Precautionary Notes

4.6.1 Consideration should be given to voltage (IR) drops other than those across the steel/water interface when structure potential data are evaluated.

4.6.1.1 Changes in water resistivity from causes such as freshwater flow from a river or temperature variation affect the included voltage drop.

4.6.1.2 In impressed current systems, under conditions involving high-resistivity water and/or high current density, the voltage drop may be excessive. Potential measurements taken immediately after turning off the rectifier(s) may provide useful information by eliminating voltage drop in the water.

4.6.1.3 In conventionally designed galvanic anode protection systems, current-off readings are not possible. However, the included voltage drop is generally not significant in ordinary seawater if the reference electrode is placed close to the structure.

4.6.2 Storm waves or strong tides can produce high water velocities that tend to depolarize the structure. Higher water levels also add additional areas of unprotected steel and increase the current required to produce protective potentials. Depolarization is less likely to be a problem for well-polarized structures with well-formed calcareous deposits or for coated steel structures.

4.6.3 Marine growth may mask the true condition of the steel surface during a visual inspection; it must be removed from the areas being inspected. All potential measurements on the structure shall be made before removal of marine growth. The removal process could depolarize the steel and might result in erroneous measurements.

4.6.4 Coupons normally are small and care must be taken in extending coupon data to cover other areas or the entire structure on protected structures.

4.6.5 The Ag/AgCl (sw) potential is somewhat affected by the resistivity, e.g., the chloride content, of the seawater in which the electrode is immersed. If the resistivity is known to differ appreciably from that of ordinary



FIGURE 1

Nomogram for the correction of potential readings made with the Ag/AgCl electrode in waters of varying resistivity to the saturated calomel or Cu/CuSO₄ scale.^{(4),9}

⁽⁴⁾ Nomogram courtesy of M.H. Peterson, Naval Research Laboratory (NRL), Washington, DC and R.E. Groover, NRL Marine Corrosion Laboratory, Key West, FL.

seawater (20 ohm-cm), the electrode reading should be corrected in accordance with the nomogram shown in Figure 1. For example, if brackish water of 100 ohmcm resistivity exists at the structure site, the minimum protective potential to Ag/AgCl electrode is -0.83 V, corresponding to -0.85 V to CSE.

4.6.6 At water depths progressively beyond 300 m (1,000 ft) and sometimes at shallower depths, seawater characteristics (dissolved oxygen, temperature, salinity, pH, sea currents, and fouling) may vary significantly from surface and shallow depths and affect cathodic polarization and calcareous deposit formation. A site-specific survey for CP performance and seasonal variation of seawater characteristics is helpful in the design of an effective CP system for deep water.

4.7 CP can affect the corrosion fatigue properties of the structure.

4.7.1 CP at typical potential values tends to restore the steel to the "in-air" fatigue value.

4.7.2 The rate of propagation of fatigue cracks may be accelerated in some steels with highly negative CP potentials. Fatigue crack growth data may be used to establish whether highly negative potentials are significant.

4.7.3 The calcareous coating may plug fatigue cracks, reducing crack growth.

4.7.4 Corrosion should be controlled in highly stressed locations to prevent pitting that might promote fatigue cracks.

Section 5: Design of Cathodic Protection Systems

5.1 Introduction

5.1.1 This section recommends procedures for designing CP systems that provide effective corrosion control for offshore structures.

5.1.2 In the design of an offshore CP system, environmental factors must be understood, and consideration should be given to the following:

5.1.2.1 Selection and specification of materials, equipment, and installation practices that ensure the safe installation and operation of the CP system.

5.1.2.2 Specification of materials and installation practices in conformance with applicable codes, regulations, and standards that may be issued by the following:

- (a) Structure operator,
- (b) NACE International,
- (c) API,
- (d) Government agencies,
- (e) National Electrical Code⁽⁵⁾ certifying agents, or
- (f) Other international standards associations

5.1.2.3 Selection and design of the CP system for optimum economy of installation, safety, maintenance, and operation. 5.1.2.4 Selection and specification of materials and installation practices that ensure dependable service for the operating life of the CP system.

5.1.2.5 Selection of a system to minimize excessive protective current densities or excessive earth (sea) potential gradients that may have detrimental effects on coatings or on neighboring buried or submerged foreign structures.

5.1.2.6 Initiation of cooperative investigations to evaluate the possible effects of the proposed CP system on the facilities of others (or their future expansion) in the general proximity.

5.2 Major Objectives of CP System Design

5.2.1 To deliver sufficient current for the design life of the facility, protect the structure, and distribute the current so that the selected criterion for CP can be efficiently satisfied.

5.2.2 To minimize the effect on associated pipelines or other neighboring metallic structures that may be caused by the operation of the proposed system.

5.2.3 To provide anode system design life commensurate with the design life of the protected structure or plan, and, when necessary, provide adequate rehabilitation procedures and appurtenances for the anode system.

⁽⁵⁾ National Fire Codes, National Electrical Code 70 (Quincy, Massachusetts: National Fire Protection Association).

5.2.4 To provide adequate allowance for anticipated changes in structure current requirements and anode current delivery capability from the standpoints of aging, additions to the structure, and possible changes in the environment.

5.2.5 To place all CP system components such that the possibility of disturbance or damage is minimal.

5.3 Information Necessary or Useful for Offshore Structure CP System Design

5.3.1 Structure construction specifications and practices:

(a) Construction drawings,

(b) Onshore construction site, offshore construction practices, and probable construction dates,

(c) Number, size, and locations of riser pipes, including electrical cables,

(d) Coatings,

(e) Availability of electrical power,

(f) Corrosion control measurement points (test stations, electrical bond locations, etc.),

(g) Safety requirements,

(h) Installation accessibility and availability of structure equipment for possible use in system installation and/or replacement,

- (i) Anticipated life of structure (design life),
- (j) Water level,

(k) Pile guides removed after piling is completed or included in the CP design, and

(I) Location of isolation flanges or standoffs.

5.3.2 Offshore site conditions:

(a) Water depth, oxygen content, velocity, turbulence, temperature, water resistivity, tidal effects, silt, sand, and suspended solids (see Appendix A),

(b) Dependability of future monitoring and maintenance, including cost factors,

- (c) Adjacent facilities, including pipelines,
- (d) Existing and proposed CP systems, and

(e) Electrical isolation from foreign pipelines or structures.

5.3.3 Field survey data, corrosion test data, and operating experience:

(a) Protective current requirements to meet applicable criterion or criteria (see Paragraph 5.6),

(b) Water resistivity (considering possible stratification of water properties),

(c) Changes in construction specifications,

(d) Electrical isolation and/or continuity,

(e) Interference currents (see Section 7),

(f) Performance history of previous or existing CP systems in the same general environment,

(g) Maximum operating temperatures of pipeline risers, and

(h) Other maintenance and operating data.

5.3.4 Complete field survey work prior to actual application of CP is not always required if previous experience and test data are available for estimating current requirements and system performance.

- 5.4 Types of CP Systems
 - 5.4.1 Galvanic anode systems

5.4.1.1 Galvanic anodes may be alloys of such active metals as magnesium, zinc, or aluminum. These alloys can be obtained in a variety of shapes and sizes to deliver protective current to a specific offshore structure with optimum current distribution. The method used to attach the anodes to the structure should be governed by their type and application, but low-resistance electrical contact must be maintained throughout the operating life of the anodes.

5.4.1.2 The performance of galvanic anodes in seawater depends critically on the composition of the alloy, particularly in the cases of zinc and aluminum (see Appendix B).

5.4.1.3 Magnesium anodes are very active and furnish high current outputs. For this reason, they can provide CP with a minimum number of anodes. Because of their properties, they usually are not used for long-life designs.

5.4.1.4 For coated structures, the galvanic anode material should be capable of supplying current even after many years of very low anodic current density.

5.4.2 Impressed current anode systems

5.4.2.1 Impressed current anode materials may include lead-silver alloy, platinum over various substrates, mixed metal oxides, lead-platinum, graphite, or silicon-iron. These anodes should be connected with an electrically insulated conductor, either singly or in groups, to the positive terminal of a direct current source such as a rectifier or generator. The structure to be protected should be connected to the negative terminal of the direct current source.

5.4.3 Combination of galvanic anode and impressed current systems

5.4.3.1 A combination CP system provides protection during structure construction and/or during times when the impressed current system is inoperative.

5.4.3.2 If the galvanic portion of the system is smaller than a conventional long-term system, it requires careful design to ensure adequate amount and distribution of current.

5.5 Considerations That Influence Selection of the Type of CP System

5.5.1 Availability of electrical power

5.5.2 Dependability of the overall system

5.5.2.1 Galvanic anode systems have shown dependability for long-term protection.

5.5.2.2 Impressed current systems are capable of providing long-term protection but are less tolerant of design, installation, and maintenance short-comings than galvanic anode (sacrificial) systems. Good service can be expected if proper attention is paid to mechanical strength, connections, cable protection (particularly in the wave or splash zone), choice of anode type, and integrity of power source. Adequate system monitoring should be provided.

5.5.2.3 Built-in redundancy, the use of appropriate design margins, and provisions at the design stage for thorough maintenance can enhance the dependability of an impressed current system.

5.5.3 Total protective current required

5.5.4 Given the current required, the feasibility of protection with galvanic anodes and selection of anode material can be established by consideration of the following (see Appendixes):

(a) Resistivity of the electrolyte,

(b) Anode-to-structure potential (when structure is at protected level),

(c) Freedom from mechanical damage in installation, launching, and operation,

(d) Useful life expectancy of anode material, and

(e) Structure weight and structural limitations.

5.5.5 The physical space available for impressed current anodes placed on the ocean floor should be determined by the proximity of other structures and pipelines and by future construction and maintenance considerations.

5.5.6 The economics of capital investment, maintenance, inspection, depreciation, taxes, and corrosion losses should be considered over the entire expected life of a CP system to assess the impact of the various alternatives properly.

5.5.6.1 A galvanic anode system requires a relatively large initial capital investment but little maintenance expense.

5.5.6.2 An impressed current anode system typically requires a lower initial capital investment with power and higher maintenance expenses added over the life of the system.

5.6 Factors Determining Total Current Requirements for $\ensuremath{\mathsf{CP}}$

5.6.1 Total submerged areas:

5.6.1.1 Water-submerged area.

5.6.1.2 Area below mudline.

5.6.1.3 On structures that may contain wells, the actual anticipated number of conductors to be installed.

5.6.1.4 Uninsulated and unprotected foreign structures.

5.6.2 Anticipated minimum protective design (or maintenance) current density requirements of submerged structure area.

5.6.2.1 Typical long-term average water zone current densities for CP of open-ocean structures that have been employed historically range from 55 to 430 mA/m² (5 to 40 mA/ft²). For values typical of 11 offshore production areas, see Appendix A. Alternatively, based on service data from offshore structures and laboratory results from test specimens, Hartt and Lemieux¹⁰ proposed that design mean current density, i_m, conform to the expression used in Equation (1):

$$i_{m} = \frac{10^{(a+c\sigma)} \times T_{d}}{b+1}$$
(1)

where:

 σ = standard deviation for the i_m data,

 T_d = design life

- $c = safety factor multiple on \sigma$, and
- a and b are constants.

Values for a, b, and σ were determined for cold and warm water locations as listed in Table 1. The

magnitude for c is selected based on the factor of safety that is judged appropriate with credit being given for system redundancy. It was shown that the design i_m values in Appendix A for cold water locations correspond to c ~ 1, whereas the Appendix A current densities exceed the i_m projected by Equation (1) for warm water locations even with c = 2, which encompasses 97.5% of the data.

	Warm/Shallow Parameters	Cold/Deep Water Parameters
σ	0.233	0.229
а	3.130	2.820
b	-0.410	-0.226

Table 1: Suggested Design Parameters for Equation (1)

5.6.2.2 Typical mud zone protective current densities are 10 to 30 mA/m² (1 to 3 mA/ft²).

5.6.2.3 An allowance should be included in the total design current requirements to compensate for the current load imposed by the well casings below the mudline. Values typically range from 1.5 to 5 A per well. For tension leg platform (TLP) and subsea production templates the well casings may be coated or cemented from total depth (TD) to the seabed, and thus greatly reduce the bare steel areas that draw current. In these cases consideration for the reduced surface area should be made, which may justify a reduction in the current allowance per well.

5.6.2.4 An allowance should be included in the total design current requirements to compensate for the current load imposed by pilings below the mudline. Values typically range from 1.5 to 5 A per piling. For subsea templates, this current demand may control the design.

5.6.3 Allowance for coatings, if any, on submerged portions of the structure.

5.6.3.1 In the past, conventional protective coatings (other than anode shields) were seldom applied to structures below the splash zone. However, increased current requirements and anode weight restrictions can affect the decision to coat complex structures to be installed in deeper waters with higher current density requirements, in shielded areas such as large conductor bundles, and/or on structures with extended design lives.

5.6.3.2 The current demand of a coated structure increases with time as the coating deteriorates. Enough CP capacity should be provided to maintain protection as the coating deteriorates. Current demand may increase more or less rapidly than a visual inspection of the coating deterioration indicates.

5.6.3.3 Calcareous coatings, formed on the structure members by the application of CP current, reduce the current density required to maintain protective potentials and also improve current distribution (see Paragraph 5.6.4). Organic coatings also promote the formation of a dense calcareous deposit at coating holidays and bare areas because the initial current density may be relatively high at such locations. However, the solubility of potential film-forming calcareous deposits normally increases with decreasing temperature such that colder waters might not allow the formation of a protective calcareous coating or could require higher initial current density to achieve polarization.

5.6.4 Efficiency of current distribution

5.6.4.1 Current distribution efficiency can be improved by use of a greater number of anodes of lower individual output. Current distribution can also be improved by using a coating on the structure.

5.6.4.2 Galvanic anode systems, being made up of numerous distributed, small current sources (typically from 3 to 6 A each) achieve maximum efficiency of current distribution. When these anodes are mounted at least 30 cm (12 in.) offset from the structure members, a uniform current distribution is normally assumed for design purposes.

5.6.4.3 Impressed current anodes, being fewer in number and designed for larger current outputs than galvanic anodes, normally have a reduced current distribution efficiency. These anodes may be designed to discharge from 30 to more than 200 A each. The high current output usually results in overprotection of the nearest structure surfaces. To compensate for the inefficient distribution of current, an efficiency factor (usually in the range of 67 to 80%) should be used. The CP system should be sized to provide 1.25 to 1.50 times

NACE International

the calculated total current requirement, using the surface areas and selected design current densities.

5.6.4.4 With either galvanic or impressed current systems, the anodes should be distributed vertically and/or horizontally in accordance with the calculated current requirements of the structure members. Computer modeling can be used to verify proper current distribution.

5.7 Factors Determining Anode Current Output, Operating Life, and Efficiency

5.7.1 Various anode materials have different rates of consumption when discharging a given current density from the anode surface in a specific environment. Therefore, for a given current output, the anode life depends on the anode material as well as on its weight. Established anode performance data should be used to calculate the probable consumption rate (see Appendixes B and C).

5.7.2 Galvanic anodes and anode systems should be designed to provide sufficient exposed anode area to produce the required protective current for the life of the anode system. Two alternative protocols for calculating anode output capability are shown in Appendixes D and E. The anode system must also provide sufficient weight of anode material to supply current for the desired number of years of protection, based on established anode performance data.

5.7.3 Proper design of a galvanic anode system must consider structure-to-anode potential and resultant anode current output and, when applicable, anode lead wire resistance. The net driving voltage between a typical aluminum-zinc-mercury or zinc anode of -1.50 V (Ag/AgCl [sw] reference) is only 0.25 V (1.05 - 0.80), although the initial net driving voltage is higher because the structure potential is more positive at this time.

The anode lifetime (L) of galvanic anodes may be determined using Equation (2):

$$L = \frac{W \times u}{E \times I}$$
(2)

where:

- L = effective lifetime of the anodes in years
- W = net mass of the anodes in kg or lb
- U = utilization factor determined by the amount of anode material consumed when the remaining anode material cannot deliver the current required
- E = consumption rate of the anode in kg/A-yr or lb/A-yr
- I = mean current output during the lifetime in A

The shape of the anode affects the utilization factor. Proper selection of length, diameter, and core diameter

NACE International

can result in utilization factors ranging from 0.75 to almost 1.0. For standoff-type anodes, utilization factors of 0.90 to 0.95 are common. For bracelet anodes, values of 0.75 to 0.90 may be used.

5.8 Special Mechanical and Electrical Considerations

5.8.1 The performance of a CP system is dependent on the ability of the various components to withstand the physical stresses to which they are subjected. The type of system, the various components thereof, and the physical installation should all be durable and dependable.

5.8.2 Galvanic anode systems are relatively simple, but consideration must be given to the following:

5.8.2.1 Anodes should be located on the structure to ensure polarization of node welds as early as possible. Node welds are critical for structural strength of structures. Polarization of node welds is of primary importance to prevent development of unacceptable weld profiles such as undercutting in the heat-affected zone (HAZ) and pitting in the weld. Both types of corrosion cause additional stress concentration that can lead to fatigue cracking. Nodes are also zones of high metal surface area and complex geometry requiring greater current density for protection and to overcome the effects of shielding. Weld consumables that can cause welds to be anodic to the steel shall not be used. Tests shall be carried out as a part of the welding pre-gualification test (WPQT).

5.8.2.2 Anode cores must be structurally suitable for the anode weight and the forces to which the anode is subjected, both during structure setting and pile-driving operations and during storms and hurricanes. It is important that the core be able to withstand anticipated wave forces in the later stages of anode consumption, when the body of the anode is no longer adding its strength to that of the anode core.

5.8.2.3 The core should be designed to maintain electrical integrity with the anode body for the full design life of the anode. A large-diameter core aids in achieving the required electrical output toward the end of the life of the anode.

5.8.2.4 Reinforcement to the structure members may be required to support the larger sizes of galvanic anodes. If so, it should be made at the point of anode attachment by gussets, doubler plates, or another approved method.

5.8.2.5 Because the efficiency of some aluminum alloys is adversely affected when they are covered with mud, attaching such anodes to structures located at or below the mudline should only be done after testing the anode in representative mud, or if experience shows that the intended anode mater-

ial does not passivate when covered by mud. The reduction in the current output and efficiency from a galvanic anode covered by mud should also be considered if it is at or below the mudline.

5.8.2.6 Whenever practicable, the larger sizes of galvanic anodes should be attached to the structure in such a manner that stresses are minimized at the point of attachment.

5.8.2.7 When the larger offshore-type anodes are used, cracks may occur while cooling during casting because of the different coefficients of expansion of the anode and the core. These cracks are not detrimental, provided they do not converge in a manner to allow loss of anode material. Warpage is acceptable if it does not adversely affect the anode installation. More specific guidelines can be found in NACE Standard RP0387.¹¹

5.8.2.8 When galvanic anodes are mounted flush with the steel surface, either the back face of the anode or the surface of the steel should be coated or fitted with a dielectric shield to prevent premature consumption of the anode material from the back face and possible failure of the mount because of the pressure developed by the corrosion products of the anode.

5.8.3 Impressed current systems are more critical with respect to mechanical damage because relatively few anodes, each discharging a substantial amount of protective current, are involved. The loss of an anode can seriously reduce system performance.

5.8.3.1 The electrical connection between the anode lead cable and the anode body must be made watertight and mechanically sound.

5.8.3.2 Cable and connection insulating materials should be resistant to chlorine, hydrocarbons, and other deleterious chemicals.

5.8.3.3 Care must be taken to provide suitable mechanical protection for both the anode and its connecting cable. On suspended systems, the individual anodes or anode strings may be equipped with winches or other retrieval means as a damage-preventing measure during severe storms or for routine inspection and maintenance. The loss of protection during these periods should be considered.

5.8.3.4 Acceptable methods of installing fixedtype impressed current anodes include, but are not limited to, the following:

(a) Anodes can be installed at the lower ends of protective vertical steel pipe casings or conduits. Casings should be attached to above-water structure members and supported at repeating members below water. The anodes should be lowered through the casings (which protect the anode lead wires) and should be allowed to extend below a termination fitting at the bottom of each casing. This method provides a means of anode retrieval or replacement using the anode cable, without diver assistance. Marine growth or corrosion scale may make anode retrieval difficult.

(b) Anodes with essentially flat configurationmounted, insulating-type holders can be attached directly to submerged structure members or to auxiliary structural members, such as vertical pipes, which can be removed for anode replacement. Properly designed sys-tems of the latter type permit anode retrieval without diver assistance.

(c) Anodes can be installed on submerged structure members using offset steel structural supports attached to the structure members. Diver assistance is required for this type of anode replacement.

(d) Anodes may be bottom-installed on the ocean floor in special instances, such as in Cook Inlet, Alaska. Anodes are typically mounted on specially designed concrete sleds for stability; this minimizes the possibility of their becoming covered with mud or silt. Steel reinforcing in the concrete has been reported to be subject to interference current corrosion.

5.8.3.5 Impressed current anodes should be located as far as practical from any structure member (usually a minimum distance of 1.5 m [5.0 ft], but proportional to current magnitude [see Paragraph 8.5.2]). If a spacing of 1.5 m (5.0 ft) is not feasible a dielectric shield should be used to minimize wastage of protective current by localized overprotecttion. Anode holders should be designed to avoid such wastage and to minimize the possibility of a short circuit between the anode and the structure. NOTE: Satisfactory performance of coating materials used as cathode shields has not been fully demonstrated over long periods of time. Providing a suitable anode-to-cathode spacing is the preferred method of ensuring good anode current distribution.

5.8.3.6 Simple, rugged, easily maintained impressed current equipment should be used. Because conditions at an offshore location seldom vary, except for weather-related factors, manually adjustable oil-cooled rectifiers with both alternating current (AC) and direct current (DC) overload protection are preferred. In certain special cases, either *constant current or automatic potential control* rectifiers may prove desirable, but the cost and maintenance of these units should be compared. 5.8.3.7 There may be a delay of several months to a year or more between the time a structure is

set until permanent electrical power becomes available. Plans should be made for either temporary power and early energizing of impressed current systems or a short-term galvanic anode system. Otherwise, serious corrosion of structure members, as well of as the underwater components of the impressed current system, can occur.

5.9 Design Drawings and Specifications

5.9.1 Suitable drawings should be prepared to designnate the overall layout of the CP system and the location of significant items of hardware, corrosion test and monitoring stations, bond boxes, insulators, and neighboring buried or submerged metallic structures.

5.9.2 Layout drawings should be prepared for each impressed current CP installation, showing details and location of its components with respect to the structure to be protected.

5.9.3 The locations of galvanic anodes should be shown on drawings or recorded in tabular form with appropriate notes as to anode type, weight, shape, and location. 5.9.4 Specifications should be prepared for all materials and installation practices to be incorporated in construction, inspection, and operation of the CP system.

5.9.5 Suitable, as-built drawings should be prepared during and at the completion of all installations. These drawings should include any deviations from original design.

5.9.6 Complete records should be maintained. Details of CP installations are necessary for trouble-shooting and future design (see Section 15).

5.10 Design of Companion Facilities

5.10.1 If the design of an offshore CP system incorporates the use of insulating flanges or unions, locating each insulating device in vertical piping minimizes internal shorting caused by accumulation of salts, metallic residue, or other conductive materials. Such insulating devices should not be located below the water line (see Paragraph 6.7.1).

5.10.2 The potential sparking hazard of insulating devices should be recognized and considered in the design and location of such devices.

Section 6: Installation of Cathodic Protection Systems

6.1 Introduction

6.1.1 This section recommends procedures for installing CP systems in accordance with design considerations outlined in Section 5.

6.2 Construction Specifications

6.2.1 All construction work performed on CP systems should be done in accordance with drawings and specifications. The construction specifications should be in accordance with procedures outlined in Sections 3, 4, and 5.

6.3 Construction Supervision

6.3.1 All construction work performed on CP systems should be done under the supervision of qualified personnel to verify that the installation is made in strict accordance with the drawings and specifications. Exceptions should be made only with the consent of the supervising corrosion specialist.

6.3.2 All changes from construction specifications should be noted on as-built drawings.

- 6.4 Galvanic Anodes
 - 6.4.1 Inspection and handling

6.4.1.1 Specific guidelines can be found in NACE Standard RP0387.¹¹

6.4.1.2 Anodes should be inspected to ensure that dimensions and weight conform to design specifications and that any damage from handling does not affect application.

6.4.1.3 In the case of weld-on anodes, the steel cores should be inspected for conformance to specifications. If the anode cores have welded joints or connections, these should be inspected to ensure compliance with structure welding specifications.

6.4.1.4 When galvanic anode suspension cables are used for the lead wire, the cables should be inspected for strength, voltage drop, and good electrical contact with the anode. When separate suspension cables are used, care should be taken to ensure that anode lead wires are not in such tension as to damage the lead wires or connections.

6.4.1.5 If coatings are specified for anode supports or suspension cables, they should be visually inspected and repaired if damaged.

6.4.2 Installing anodes

6.4.2.1 Anodes should be installed according to construction specifications.

6.4.2.2 When anodes are welded directly to the structure, the welds should be inspected for conformance to the structure construction welding specifications.

6.4.2.3 Use of doubler and/or gusset plates should be considered for anodes mounted on standoff pipe cores and weighing more than 230 kg (500 lb).

6.4.2.4 Doubler and/or gusset plates may be installed on anode supports at the time of anode installation. If installed as part of the anode fabrication, these plates may be subject to serious damage during anode hauling and handling.

6.4.2.5 Suspended galvanic anodes should be installed after the structure is set on location offshore, and the anode cables should be tested for good electrical contact to the structure after installation.

6.5 Impressed Current Systems

6.5.1 Inspection and handling

6.5.1.1 The rectifier or other power source should be inspected to ensure that internal connections are mechanically secure and that no damage has occurred during shipping and handling. Nameplate and actual rating of the direct current power source should comply with construction specifications.

6.5.1.2 Impressed current anodes should be inspected for conformance to specifications for anode material and size and length of lead wire and to ensure that the anode cap (if specified) is secure. Lead wires should be carefully inspected to detect possible insulation defects. Defects in the lead wires and/or anode caps must be properly repaired or the anode must be rejected.

6.5.1.3 Care should be exercised in handling all impressed current system components prior to final installation.

6.5.2 Installation provisions

6.5.2.1 A rectifier or other power source should be installed out of the way of operational traffic and remote from areas of extreme heat or likely contamination by mud, dust, water spray, etc. In areas in which two or more rectifiers are installed, the rectifiers should be spaced for proper flow of cooling air.

6.5.2.2 Wiring to rectifiers shall comply with any applicable regulatory codes and with the oper-

ator's specifications. An external disconnect switch in the AC wiring to the rectifier should be provided. The rectifier case shall be properly grounded. Connecting the negative to the case prevents inadvertent reversal of polarity.

6.5.2.3 On thermoelectric generators, a reverse current device should be installed to prevent galvanic action between the anode and structure if the flame is extinguished.

6.5.2.4 Impressed current anodes should be installed in accordance with construction specifications. Special care should be taken to avoid damage to anodes and their lead wires during installation. Careful supervision of this phase is most essential to proper long-term performance of the CP system.

6.5.2.5 Conductor cable connections to the rectifier from the anode(s) and the structure must be mechanically secure and electrically conductive. Before the power source is energized, verification should be made that the negative (-) conductor is connected to the structure to be protected, that the positive (+) conductor is connected to the anode(s), and that the system is free of short circuits.

6.5.2.6 Connection between the positive header cable and lead wire(s) from the anode(s) should be mechanically secure and electrically conductive. The connections must be sealed to prevent moisture penetration and ensure electrical isolation from the environment. Submerged connections require seals suitable for the water pressures and environment to which they may be subjected.

6.5.2.7 When installing a suspended anode for which separate suspension is required, care should be taken that the lead wire is not in such tension as to damage the anode lead wire or connections.

6.5.2.8 Operating personnel should be trained in the function and need for such a system to ensure continued energization of the system.

6.6 Corrosion Control Test Stations, Connection, and Bonds

6.6.1 Installation provision

6.6.1.1 Test leads to pipelines associated with offshore structures must be mechanically secure and electrically conductive and should be readily accessible.

6.6.1.2 Both the pipe and the test lead wires should be clean, dry, and free of foreign material at points of connection when the connections are

made. The complete connection should be coated to prevent atmospheric corrosion.

6.6.1.3 Conductive connections to other pipelines or across insulating joints should be installed in accordance with Paragraph 6.6.1.1. All bond connections should be readily accessible for testing. Cables should have welded connections. Care should be taken to ensure that all parts of the structure are in proper electrical contact with one another or are equipped with separate anodes.

6.7 Other Considerations

6.7.1 Insulating devices

6.7.1.1 Use of insulating flanges in pipelines associated with structures is covered in Paragraph 5.10.1. If insulating flanges above water are inaccessible, extension test leads should be installed in accordance with Paragraph 6.6.1.1 for test or bonding purposes.

Section 7: Control of Interference Currents

7.1 Introduction

7.1.1 The purpose of this section is to describe the possible detrimental effects of interference currents, sometimes called stray currents, and to recommend practices for their control.

7.1.2 Except during certain types of welding operations, the possibility of interference current corrosion on offshore structures is minimal.

7.2 Effects

7.2.1 Corrosion occurs in areas at which the interference current leaves the affected structure and enters the electrolyte as it returns to its source.

7.2.2 The degree of damage is directly related to:

(a) the quantity of interference current and the current density,

(b) the area of the affected structure where the current leaves to enter the electrolyte, and

(c) the period of time when this effect occurs.

7.3 Short-Term Interference

7.3.1 The most common serious cause of short-term interference to a structure is welding operations when the welding machine is mounted on a barge or vessel with the machine's negative terminal grounded to the vessel and with the electrodes positive. Some operators have reported serious damage to structures with complete penetration of the submerged member as a result of welding current interference. The following measures should be implemented to prevent interference current during welding operations from a barge moored alongside during construction: (a) All welding machines should be electrically isolated from the barge, and (b) the grounding cable from each machine should be connected to the structure. Alternatively and preferably from a corrosion standpoint, the barge oper-

ator should place the welding machines on the structure.

7.3.2 When negative welding leads are bonded to the structure, current return is ostensibly through negative leads or cables connected to the structure, but is also to some degree through the parallel water path from structure to barge hull if the precautions of Paragraph 7.3.1 are not followed. Current return through the water can be reduced by decreasing the resistance of the negative cables, by increasing their number and/or diameter, and by decreasing their length. Negative cables should be connected to the structure at a point as close to the barge as possible.

7.4 Long-Term Interference

7.4.1 There are normally no long-term interference sources that would cause significant corrosion on a structure, if all components of the structure are properly bonded.

7.4.1.1 The submerged, bare structure area is usually very large with respect to exposed pipeline areas; consequently, pipeline protection currents have a negligible interference effect on the structure.

7.4.1.2 The location of interference current sources and the physical arrangement of a protected structure are usually such that there is no tendency for significant interference to exist.

7.4.2 In certain cases, interference may be produced on a foreign pipeline when it is electrically isolated from a protected structure, because of the structure's CP system. Such interference can readily be controlled by the use of a current drainage bond from the pipeline to the structure, by installing CP on the isolated pipeline, or by upgrading the existing CP system on the pipeline. These mitigation procedures should be performed in cooperation with other companies or operators, when applicable.

NACE International

Section 8: Dielectric Shields

8.1 Introduction

8.1.1 This section recommends practices for the selection and use of dielectric shields, including shield configurations and materials, for CP of structures.

8.2 General

8.2.1 The objective of dielectric shields, and coatings used as dielectric shields, is to prevent extremely high current densities and current wastage in the vicinity of the anodes. This serves to promote more uniform protective current distribution.

8.3 Use of a Dielectric Shield

8.3.1 Use of a dielectric shield depends on the CP design (see Section 5). Typically, dielectric shields are used in conjunction with an impressed current system because higher voltage gradients are generally used in such systems. A dielectric shield may also be used with a high-potential galvanic anode such as magnesium.

8.3.2 Specific uses of dielectric shields, including coatings used as dielectric shields, are as follows:

(a) to cover cathode surfaces adjacent to anodes,

(b) to provide a nonconducting extension to steel pipe conduits for impressed current anodes,

(c) to afford a backing for flush-mounted galvanic anodes,

(d) to minimize current demand by structure members in highly congested areas, and

(e) to restrict anode current output, i.e., reduce wastage of anode current to the structure in the immediate vicinity of the anode.

8.3.3 A general underwater coating may be considered as a type of dielectric shield and can be used either to reduce the required current or to extend the life of a CP system.

8.4 Types of Dielectric Shields

8.4.1 Various dielectric shields have been used in structure CP. These include yard-applied coatings, prefabricated plastic or elastomeric sheets, plastic pipe sleeves, and coated standoffs or supports for impressed current anodes.

8.5 Design Considerations

8.5.1 Electrochemical reactions at the anode and cathode produce corrosives and gases that may attack the dielectric shield or cause disbonding by gas formation under the dielectric shield. Materials selected should be suitable for the intended service.

8.5.2 For proper performance, the design of the dielectric shield (radius around the anode or distance from the anode to the nearest bare cathode surface) must involve considerations of the anode current output, the water resistivity, the geometry of the structure, and the location of other anodes.

8.5.3 Mechanical damage from environmental factors such as wave forces, water currents, floating debris, ice, and marine organisms must be considered. The design shall also include allowances for possible hand-ling damage prior to structure placement.

8.5.4 The anticipated life or general deterioration of any dielectric shield material should be considered in the CP design (see Paragraph 5.8.3.4).

Section 9: Operation and Maintenance of Cathodic Protection Systems

9.1 Introduction

9.1.1 This section designates procedures for energizing and maintaining continuous, effective, and efficient operation of CP systems.

9.2 Electrical Measurements

9.2.1 Electrical measurements and inspections are necessary to determine that protection has been established according to applicable criteria and that each

part of the CP system is operating properly. Conditions that affect protection are subject to change with time. Corresponding changes are required in the CP system to maintain protection. Periodic measurements and inspections are necessary to detect performance changes in the CP system.

9.2.2 Care should be exercised in selecting the location, number, and type of electrical measurements used to determine the adequacy of CP (see Section 4). 9.2.3 Conditions may exist in which operating experience indicates that surveys and inspections should be made more frequently than recommended herein, such as following severe storms.

9.3 A survey should be conducted after each CP system is energized to determine whether it satisfies applicable criteria and operates effectively. This survey must include structure potential measurements in sufficient detail to demonstrate conclusively that protection has been attained (see Section 4).

9.4 A periodic survey should be made to ensure the continuity of CP. The electrical measurements used in this survey should include structure potential measurements at locations selected for the earlier survey(s). The period between surveys should be determined as follows:

9.4.1 If previous survey data are not available, or no analysis of the previous data has been carried out, the survey should be carried out annually.

9.4.2 For sacrificial anode CP systems there are two critical periods of operation—initial operation of the system, demonstrating that the entire structure is polarized (see Paragraph 9.3); and final years of design life of the system, when the performance of the anodes can become more difficult to predict. Between these periods structure potentials and anode wastage rates follow well-defined trends. Taking this into account, a risk-based approach to CP inspection can be adopted. Inspection frequency should be based on a five-year interval unless more frequent inspection is required because of any of the following conditions being present:

- Visual inspection reveals additional steelwork on the structure not included in the current structure CP drawings. This could include debris in electrical contact with the structure, new conductors, new caissons, new risers, etc. A CP survey should be carried out immediately, structure potentials measured, structure CP drawings updated, the impact on the structure anode design life assessed, and the need for any remedial work assessed (e.g., removal of debris, installation of additional anodes, etc.).
- Anodes are within two years of the end of their original design life. The CP survey should be carried out annually. If the required structure life is in excess of the remaining anode design life, the actual remaining life of the anode system should be reassessed (based on a survey of potentials and remaining anode mass) and the need for a retrofit assessed. If the original CP design was conservative, the actual remaining anode life may be well in excess of two years. This actual

remaining anode life can be used in scheduling future CP surveys (on the same five-year/two-year basis).

 Local regulatory requirements that require more frequent inspections (e.g., U.S. Minerals Management Service⁽⁶⁾—annual).

9.4.3 For impressed current cathodic protection (ICCP) systems the initial operation of the system is critical, demonstrating that the entire structure is polarized (see Paragraph 9.3). After this, the performance of the ICCP system depends on proper operation and maintenance (see Paragraph 9.5). Taking this into account, a risk-based approach to CP inspection can be adopted. Inspection frequency should be based on a five-year interval unless more frequent inspection is required because of any of the following conditions being present:

- Visual inspection reveals additional steelwork on the structure not included in the current structure CP drawings. This could include debris in electrical contact with the structure, new conductors, new caissons, new risers, etc. A CP survey should be carried out immediately, structure potentials measured, structure CP drawings updated, the impact on the ICCP system assessed, and the need for any remedial work assessed (e.g., removal of debris, installation of additional anodes, modified anode currents, etc.).
- Operation and maintenance of the ICCP shows poor functionality, which indicates damaged anodes or cables
- Local regulatory requirements that require more frequent inspections (e.g., U.S. Mineral Management Service—annual).

9.5 Inspection and tests of ICCP facilities should be made to ensure their proper operation and maintenance.

9.5.1 All sources of impressed current should be checked at intervals not to exceed two months. Evidence of proper functioning may be current output, normal power consumption, or satisfactory structure-to-seawater potentials on the protected structure.

9.5.2 All ICCP facilities should be inspected annually as part of a preventive maintenance program to minimize in-service failure. Inspection may include a check for electrical shorts, satisfactory ground and header cable connections, meter accuracy, rectifier efficiency, and overall circuit resistance.

⁽⁶⁾ Bureau of Mines, 2402 E Street NW, Washington, DC 20241.

9.6 The test equipment used for obtaining each electrical value should be maintained in good operating condition and checked annually for accuracy. Reference electrodes should be checked more frequently for possible inaccuracy because of contamination, bad electrical connections, or deterioration of wire insulations.

9.7 Diver-assisted or ROV inspections may be conducted in conjunction with other underwater work to ensure that the CP system is effective.

9.8 Remedial measures should be taken promptly when periodic surveys and inspections indicate that protection is

no longer adequate or will soon become inadequate. These measures may include:

9.8.1 Repairing, replacing, or adjusting components of CP systems.

9.8.2 Providing supplementary CP facilities in areas where additional protection is necessary.

9.8.3 Repairing defective insulating devices or continuity bonds.

Section 10: Splash Zone Corrosion Control Measures

10.1 Introduction

10.1.1 This section lists corrosion control measures that minimize the deterioration of steel members in the splash zone. Some procedures may not be applicable in all areas of the world because of varying service conditions.

10.1.2 Corrosion of attached pipelines or risers in the splash or submerged zone is outside the scope of this standard.

10.1.3 Additional thickness of steel is usually provided in the splash zone.

10.2 Placement

10.2.1 Unless the setting depth of the structure can be ensured, consideration should be given to additional protection beyond the normal splash zone interval to provide a margin of safety.

10.3 Steel Wear Plates and Corrosion Allowance

10.3.1 Wear plates should compensate for the anticipated corrosion and wear during the life of the structure. Wear plates are usually 13 to 19 mm (0.50 to 0.75 in.) thick.

10.3.2 Wear plates are needed because damage can occur to coatings or sheathings used in the splash zone.

10.3.3 In addition to providing a corrosion allowance, wear plates add stiffness and strength, thereby providing greater impact resistance.

10.3.4 Wear plates are usually coated or sheathed for additional corrosion protection.

10.3.5 Corrosion allowance by additional steel thickness may be used instead of wear plates. The thickness should be calculated based on estimated lifetime of the installation and anticipated corrosion rate. It is normally not less than 6 mm (0.25 in.). The corrosion rate in the splash zone is typically in the range 0.2 to 0.4 mm (0.007 to 0.015 in.)/year.

10.4 Alternative Corrosion Control Measures for Steel in the Splash Zone

10.4.1 UNS⁽⁷⁾ N04400 (Nickel-copper alloy 400) or UNS C70600 (90/10 copper-nickel alloy) sheathing

10.4.1.1 UNS N04400 sheathing, typically 1 to 5 mm (40 to 200 mils) thick (18 to 4 AWG,⁽⁸⁾ or UNS C70600 sheathing, typically 4 to 5 mm (160 to 200 mils) thick, should be attached to tubular members in the splash zone either by banding or welding. Welding is preferred because the annulus between the steel member and the sheathing is sealed.

10.4.1.2 The metal sheathing should be protected from impact damage. Alloy-clad steel plate may aid in preventing damage.

10.4.2 Vulcanized chloroprene

10.4.2.1 Vulcanized chloroprene is typically applied in thicknesses of 6 to 13 mm (0.25 to 0.50 in.).

⁽⁷⁾ Metals and Alloys in the Unified Numbering System (latest revision), a joint publication of ASTM International and the Society of Automotive Engineers (SAE), 400 Commonwealth Drive, Warrendale, PA 15096.
⁽⁸⁾ American Wire Gauge (AWG): A particular series of diameters and thicknesses established as a standard in the United States and used

^{vo} American Wire Gauge (AWG): A particular series of diameters and thicknesses established as a standard in the United States and used for nonferrous sheets, rods, and wires. Also known as the Brown and Sharpe Gauge.

10.4.2.2 Because this coating cannot be applied in the fabrication yard, it is normally restricted to straight runs of tubular members.

10.4.2.3 A minimum of 50 mm (2.0 in.) should be left uncoated at each end of a tubular member to prevent damage to the chloroprene during the welding operations.

10.4.3 High-build organic coatings

10.4.3.1 These coatings are usually filled with silica glass-flake or fiberglass.

10.4.3.2 These coatings are typically applied to thicknesses of 1 to 5 mm (40 to 200 mils) over an abrasive blast-cleaned surface.

10.4.3.3 Because this coating may be applied in the fabrication yard after assembly, joints may be protected as well as straight tubular runs.

10.4.3.4 To improve inspection possibilities, an antifouling coating may be applied on the coated members. Antifouling coatings are effective up to about 10 years.

10.4.4 High-performance structure coating systems 250 to 500 μm (10 to 20 mils)

10.4.4.1 Although some high-performance coating systems currently used to protect the atmospheric zone have performed reasonably well in the splash zone, they are not suited as a primary control measure for long-life structures.

10.4.5 Heat-shrink sleeves. NOTE: Heat-shrink sleeves have not performed well in the North Sea.

10.4.5.1 Heavy plastic sleeves that shrink when exposed to an elevated temperature and are precoated internally with a sealant adhesive have been used to protect straight tubulars in the splash zone. If the sleeve is slightly damaged, the viscoelastic nature of the sealant in combination with the remaining radial shrink forces of the sleeve causes the sealant to flow to the damage site and effectively seal over the damage. Surface preparation to remove rust and coarse roughness is required.

10.4.6 Thermal-sprayed aluminum

10.4.6.1 Thermal-sprayed aluminum (either flame or arc) applied to 200 μ m (8 mils) and sealed with a silicone sealer have been used in the splash zone. Good surface preparation and cleanliness are essential. The coating should be applied in a minimum of two passes. The sealer seals the porosity of the coating and enhances service life and appearance. U.S. Military Specification MIL-STD-2138¹² offers guidelines for application and quality control.

10.4.6.2 Coating adhesion should exceed 7,000 kPa (1,000 psi). Laboratory adhesion tests may be performed using ASTM C 633.¹³ Field testing for adhesion may be performed with commercial instruments.

10.4.6.3 Thermal-sprayed aluminum has also been used in submerged and marine atmospheric services. For submerged areas this system is a candidate for areas in which protective CP potentials may be difficult to achieve, such as the underside of clamps and other geometrically shielded areas.

10.4.7 Petrolatum/wax-based tape systems

10.4.7.1 Petrolatum/wax-based coating systems with appropriate jacketing for mechanical protection may be employed.

10.4.7.2 Proper consideration shall be given to the mechanical stresses to be encountered in service by the coating system, and the protective jacketing system shall be selected to assure adequate mechanical protection.

Section 11: Maintenance of Splash Zone Corrosion Control Measures

11.1 This section lists inspection procedures and follow-up maintenance necessary to ensure continued protection of the structural steel located in the splash zone.

11.2 Inspection

11.2.1 The splash zone interval should be visually inspected annually to determine whether corrosion control is still effective. If failure has occurred, the extent of damage to underlying structural members should be assessed and corrective action taken.

11.2.2 When wear plates are used and the protective coating system has either deteriorated or been mechanically damaged, periodic wall thickness measurements should be made to determine that the loss does not exceed the corrosion allowance.

- 11.3 Repair Methods
 - 11.3.1 UNS N04400 sheathing

11.3.1.1 Tears in the UNS N04400 sheathing should be trimmed and repaired by welding or banding a UNS N04400 patch to the affected area.

11.3.1.2 An alternative procedure, which can also be performed at the water line, involves blast cleaning the damaged area after trimming the torn UNS N04400 and hand applying a thick coat of polysulfide rubber with air cure accelerator or splash zone barrier compound. The latter is a polyamide-cured epoxy formulated to displace water and cure underwater. If the area is exposed to wave action, it may be necessary to hold these compounds in place with wire mesh or burlap until the cure is complete

11.3.2 Vulcanized chloroprene

11.3.2.1 The procedure outlined in Paragraph 11.3.1.2 should be followed.

11.3.3 High-build organic coatings

11.3.3.1 Damaged areas may be repaired by spray or hand application of the original coating to an abrasive blast-cleaned surface or as outlined in Paragraph 11.3.1.2.

11.3.4 Heat-shrink sleeves

11.3.4.1 The steel surface should be cleaned, and any sharp projections should be removed.

11.3.5 Fiberglass wraps with water-activated resin

11.3.5.1 The steel surface should be cleaned to remove marine growth, and any sharp projections should be removed.

11.3.5.2 This system may use an initial sealer wrap to isolate the steel surface from seawater effectively. The outer fiberglass wrap provides a mechanical barrier.

11.3.6 Mastic-backed rubber wraps

11.3.6.1 The steel surface should be cleaned to remove marine growth, and any sharp projections should be removed.

Section 12: Surface Preparation

12.1 Introduction

12.1.1 This section recommends procedures for the proper surface preparation of structural steel shapes to be coated for service in the atmospheric zone of fixed offshore structures.

12.2 General

12.2.1 The objectives of surface preparation for steel in the atmospheric zone are to provide the necessary degree of cleanliness and the specified anchor pattern required for the designed coating system.

12.2.2 Automated blast-cleaning machines are economically desirable as a means of preparing plate, beams, and tubular members prior to fabrication.

12.2.3 The completed structure should be inspected to locate damaged or improperly primed areas prior to topcoating. Damaged areas and all weld areas require spot blasting and priming with the same material prior to completing the coating system.

12.2.4 All surface imperfections such as slivers, laminations, welding flux, weld spatter, and underlying mill scale exposed before or during operations shall be removed prior to surface preparation. 12.2.5 Surface preparation performed outside should be completed during daylight hours with the surface temperature above the dew point for that day, early enough to permit proper priming of the surface prior to the development of any moisture or flash rusting of the prepared surface. Tests for soluble salts should be performed prior to coating when the presence of any soluble salt on the prepared surface is suspected.

12.2.6 At the time of surface preparation or priming the surface temperatures shall be 3°C (5°F) or more above the dew point. Under no condition should a steel surface be conventionally coated while it is damp or wet.

12.2.7 If properly performed with containment, wet abrasive blasting may provide adequate surface preparation and reduce the dust problem created by dry blasting. However, if this type of cleaning is used, the coating systems must be compatible with the rust inhibitor used in the water blasting system. The surface prepared for coating must be dry and contaminant-free prior to coating.

12.2.8 Solvent or detergent degreasing shall be performed in accordance with SSPC $^{(9)}$ SP 1. 14

⁽⁹⁾ SSPC: The Society for Protective Coatings, 40 24th St., 6th Floor, Pittsburgh, PA 15222-4656.

12.2.9 Hand cleaning should be discouraged and should be used only for small areas where other methods of surface preparation cannot be used. Methods resulting in polishing of the steel surface, e.g., wire brushing, shall not be used.

12.3 NACE Surface Preparation Standards

12.3.1 The selection of the degree or grade of surface preparation should be determined by the requirements of the coating selected. Following are descriptions of the four degrees of abrasive blast-cleaned surfaces as given in joint NACE/SSPC standards.

12.3.1.1 NACE No. 1/SSPC SP 5¹⁵ states that a white metal blast-cleaned surface, when viewed without magnification, shall be free of all visible oil, grease, dust, dirt, mill scale, rust, coating, oxides, corrosion products, and other foreign matter.

12.3.1.2 NACE No. 2/SSPC SP 10¹⁶ states that a near-white metal blast-cleaned surface, when viewed without magnification, shall be free of all visible oil, grease, dust, dirt, mill scale, rust, coating, oxides, corrosion products, and other foreign matter. Random staining shall be limited to not more than 5% of each unit area of surface (approximately 58 cm² [9.0 in.²]), and may consist of light shadows, slight streaks, or minor discolora-

tions caused by stains of rust, stains of mill scale, or stains of previously applied coating.

12.3.1.3 NACE No. 3/SSPC SP 6¹⁷ states that a commercial blast-cleaned surface, when viewed without magnification, shall be free of all visible oil, grease, dust, dirt, mill scale, rust, coating, oxides, corrosion products, and other foreign matter. Random staining shall be limited to no more than 33% of each unit area (approximately 58 cm² [9.0 in.²]) of surface and may consist of light shadows, slight streaks, or minor discolorations caused by stains of rust, stains of mill scale, or stains of previously applied coating.

12.3.1.4 NACE No. 4/SSPC SP 7¹⁸ states that a brush-off blast cleaned surface, when viewed without magnification, shall be free of all visible oil, grease, dirt, dust, loose mill scale, loose rust, and loose coating. Tightly adherent mill scale, rust, and coating may remain on the surface. Mill scale, rust, and coating are considered tightly adherent if they cannot be removed by lifting with a dull putty knife.

12.3.1.5 A cross-index of various surface preparation standards is provided in Table 2.

Table 2: Surface Preparation Standards

Standard	White	Near-White	Commercial	Brush-Off	
NACE	No. 1	No. 2	No. 3	No. 4	
SSPC	SP 5	SP 10	SP 6	SP 7	
ISO ^(A) 8501-1 ¹⁹	Sa 3	Sa 2-1/2		Sa 1	

^(A) International Organization for Standardization (ISO), 1 rue de Varembe, Case Postale 56, CH-1121 Geneve 20, Switzerland.

12.4 Centrifugal Wheel Cleaning—This method is applicable to a fabrication plant where new weldments can be processed through an automated, wheel-type machine using metal abrasives. The cost of wheel blast surface preparation is significantly lower than the cost of air blast surface preparation work.

12.4.1 *Good Painting Practice, SSPC Painting Manual*,²⁰ should be referred to for centrifugal blast cleaning.

12.4.2 Special consideration should be given to:

12.4.2.1 Abrasive material—Steel grit of the appropriate mesh size and hardness should be used to produce the required surface profile using

the equipment selected to perform the work. Steel shot is not recommended for surface preparation for coatings to be used in severe surface applications.

12.4.2.2 Surface profile tests should be conducted and recorded on a regular agreed basis to ensure that the prepared surface of the components meets the cleanliness and profile requirements of the coating to be applied.

12.5 Air Blast Cleaning—This method is used when components are not suitable for the available automated machines, when cleaning is performed on the job (field) location, or when maintenance work is performed on offshore structures. Abrasives used are described in Paragraph 12.5.2.

12.5.1 Air supply—Initial inspection of the air supply should include the following:

12.5.1.1 Air supply capacity shall be sufficient to obtain 690 kPa (100 psi) air pressure at all operating nozzles.

12.5.1.2 Compressor shall be equipped with all properly operating safety equipment required.

12.5.1.3 Oil/moisture separators with properly maintained filters must be used in air lines. These shall be tested at least once each shift in accordance with ASTM D 4285.²¹

12.5.2 Abrasives—The blast-cleaning abrasive used for surface preparation shall be limited to the type specified in the contract documents and shall be of appropriate size to produce the required profile using the equipment available for the job. The abrasive must be clean and graded to a uniform standard size. See *Good Painting Practice, SSPC Painting Manual.*²⁰

12.6 Safety equipment for surface preparation should include, but shall not be limited to, the following:

(a) Bureau of Mines⁽¹⁰⁾ or equivalent agency-approved airfed blast hood, properly fitted, with good vision,

(b) Charcoal-filtered and regulated compressed breathing air supply,

(c) Operator-controlled deadman remote control valves,

(d) Operator protective clothing, gloves, etc.,

(e) Operator safety belts,

- (f) Proper scaffolding, and
- (g) Proper lighting.

12.6.1 Air blast operators must have proper training for effective operation of surface preparation and safety equipment.

Section 13: Coatings

13.1 Introduction

13.1.1 This section outlines general considerations relating to structure coatings and lists the generic composition of the coatings commonly used by offshore operators.

13.2 General

13.2.1 Conventional paints, surface preparation, and methods of application should not be used in extremely corrosive offshore environments. Because the maintenance cost on location is extremely high, only high-performance protective coating systems should be specified. Proper application and performance requirements of these systems demand rigorous surface preparation (see Section 12) and skilled craftsmanship in coating application and inspection (see Section 14). This can be achieved only through the enforcement of detailed and complete job specifications.

13.2.2 Proper application of high-performance coating systems requires that personnel observe and adhere to all applicable safety rules and regulations.

13.3 Coating Systems

13.3.1 Offshore coating systems are normally composed of primer, intermediate, and finish coats. Many generic coating materials are available but only a few are considered by many owners and coating consultants to be suitable for offshore service.

13.3.2 Most coating systems are based on a highly inhibited prime coat designed to have superior wetting and adhesion properties to retard undercutting by rust, and to passivate the surface. Commonly used prime coats include:

13.3.2.1 Wash primers—These are conversion coatings consisting of a vinyl butyrate resin solvent solution, pigmented with zinc or strontium chromate. Prior to application, these coatings are mixed with a second component consisting of a solution of alcohol and phosphoric acid. They are applied as very thin films not to exceed 13 μ m (0.50 mil) dry. On contact with the iron surface, they generate a passive iron phosphate layer. Wash primers must be quickly topcoated for maximum effective-ness and to prevent rust breakthrough.

13.3.2.2 Zinc-rich primers—These primers are organic or inorganic coatings with a high loading of zinc dust. When there is a rupture or discontinuity in the coating system, the zinc pigment particles protect the substrate by galvanic action. Because zinc reacts readily with both acids and strong alkalies, zinc-rich primers must be topcoated with chemically resistant coatings when used offshore because of exposure to alkaline drilling mud and acidic well-completion fluids. Zinc-rich primers are

⁽¹⁰⁾ Bureau of Mines, 2402 E. Street NW, Washington, DC 20241.

excellent preconstruction primers because of their abrasion and impact resistance and ability to protect the steel during long construction cycles. However, care must be taken to ensure that the zinc-primed surface is clean prior to topcoating. Fresh-water washing or power scrubbing may be required to remove contaminants.

13.3.2.3 Organic inhibitive primers-These materials may be solvent-based, chemically cured coatings, or thermoplastics, which form films by solvent evaporation. Chemically cured coatings generally require mixing of a second component for curing. Characteristically, these coatings include inhibiting pigments that must meet regulatory standards and limitations and be environmentally safe. On contact with moisture, the pigments generate either alkaline or ionic conditions that retard the corrosion of the base metal. Because these primers generally contain reactive pigments and are only part of a protective coating system, they must be protected with topcoats to perform as effective environmental barriers. Primers must conform to all applicable regulations regarding toxicity, safety, and environmental standards.

13.3.3 Topcoats—Primers used for offshore structures should be overcoated with intermediate and/or finish coats. These coatings function as barriers, retarding and restricting the permeation of water vapor, oxygen, and active chemical ions. Topcoats may also provide added impact resistance and solvent resistance, as well as an aesthetically pleasing finish. Generic characteristics of topcoats include the following:

13.3.3.1 Chemically Cured Coatings-These materials are usually epoxies, epoxy phenolics, polyesters, or some polyurethanes that are cured by mixing with a second component commonly called a "catalyst" or converter. These coatings, which are often applied in films exceeding 100 µm (4 mils) thickness per coat, have excellent chemicalresistant properties. Because these materials continue to cure on exposure, they become increasingly hard, brittle, and solvent-resistant with Therefore, recoating may require sweep ade. blasting to achieve good mechanical bonding. With the exception of some polyurethanes, these coatings tend to chalk on exposure to ultraviolet light. These materials tend to be temperature- and moisture-sensitive during curing and require adequate temperatures and humidity control to crosslink and develop into chemically resistant films.

13.3.3.2 Solvent-Deposited or Thermoplastic-Type Coatings—These materials include vinyl acrylics, vinyls, or chlorinated rubbers. These coatings dry by the evaporation of solvents, which distinguishes them from epoxies, polyesters, and other chemically cured coatings. The change from a liquid to a solid state is not accompanied by any chemical change. This mode of drying permits coating application at relative humidities of up to 90% and temperatures as low as 0°C (32°F). These coating films generally exhibit excellent resistance to environmental conditions. These solvent-soluble films simplify overcoating by providing solvent bonding between a refresher and previous coat. Principal disadvantages of these coating materials are limited temperature resistance (60 to 77°C [140 to 170°F]), reduced solvent resistance, and low solids-by-volume content. Because of the low solids-by-volume content, additional coats may be required to achieve the desired thickness. Recent technology indicates greater film and solidsby-volume capabilities may reduce the number of coats previously required. However, their chemical resistance may be impaired. Furthermore, regulations regarding volatile organic compounds (VOC) limitations may prohibit the application of the materials in some localities.

13.3.4 Thermal-sprayed aluminum

13.3.4.1 Thermal-sprayed aluminum (either flame or arc) applied to 200 μ m (8 mils) and sealed with a silicone sealer has been used in atmospheric service for specific applications such as flare booms. Good surface preparation and cleanliness are essential. Ninety-nine percent or higher-purity aluminum or Al-5Mg is most commonly used with two or more spray passes used in the application. The sealer enhances service life and appearance. U.S. Military Specification MIL-STD-2138¹² offers guidelines for application and quality control.

13.3.4.2 Coating adhesion should exceed 7,000 kPa (1,000 psi) (see Paragraph 10.4.6.2).

13.4 Criteria for Coating Selection

13.4.1 Accelerated tests designed for coating selection include:

(a) Salt spray testing (4,000 h) in accordance with ASTM B 117. 22

(b) Weatherometer testing (2,000 h) in accord-ance with ASTM G 152, 23 ASTM G 153, 24 ASTM G 154, 25 or ASTM G 155. 26

(c) Humidity cabinet testing (4,000 h) in accordance with ASTM D 2247. $^{\rm 27}$

Some operators run combinations of the above tests on a rotating basis, such as 1,000 h in salt spray, 1,000 h in a weatherometer, followed by an additional 1,000 h in salt spray, and a final 1,000 h in a weatherometer.

13.4.2 Other coating properties that can be determined from laboratory tests and that may aid in evaluating materials are:

ASTM D 52228

ASTM C 633¹³

ASTM D 968²⁹

ASTM D 335930

ASTM D 3363³¹

ASTM D 421432

Equivalent tests from organizations other than ASTM may be used.

13.4.3 The coating system ultimately selected depends on many environmental, application, and performance considerations, including the following:

13.4.3.1 The length of time primed steel is stored during construction periods and resistance to abrasion associated with handling and fabrication with a minimum of damage.

13.4.3.2 Coating systems that can be applied and maintained with conventional and readily available application equipment.

13.4.3.3 Cold temperatures and inclement weather restrictions for structures placed in northern latitudes.

13.4.3.4 Chemically cured coatings that have high impact resistance and resistance to spills of solvents and corrosive chemicals are often used on the deck areas of offshore structures because of anticipated exposure to weathering, abrasion associated with drilling operations, and spills of drilling mud, formation fluids, diesel fuels, lubricants, and well-completion compounds.

13.4.3.5 Offshore coatings are exposed to highintensity ultraviolet light and should be resistant to heavy chalking and color fade.

13.4.3.6 Coating systems that are easily repaired and maintained are usually preferred.

13.4.3.7 Inorganic zinc-rich primers, when damaged and exposed in service, do not readily accept another coat of inorganic zinc-rich primer (IOZ), and are normally repaired with an organic zinc-rich coating or chemically cured, inhibited primer.

13.5 Storage, Handling, and Mixing of Materials

13.5.1 All materials used in the initial or maintenance coating of offshore structures should be furnished in the manufacturer's original, unopened container, clearly labeled to identify the contents. The materials should be stored in a manner that prevents exposure to

weather extremes, with 10 to 32°C (50 to 90°F) being optimum.

13.5.1.1 Thinners, diluents, or clean-up materials should comply with the coating manufacturer's recommendation, or if independently purchased, they should be of compositions approved by the coating manufacturer.

13.5.1.2 Single-supplier responsibility should be maintained by using primers, intermediates, and finish coatings from the same supplier.

13.5.1.3 All coating materials should be thoroughly agitated prior to application. If there is settling of the pigment, it should be redispersed with a power agitator to form a uniform mixture. For two-component materials, the catalyzed mixture also should be agitated with a power mixer. For heavily pigmented coating, such as zinc-rich primer, agitation should be continued during application to prevent settling.

13.5.1.4 Mixed coating solutions should be strained through a 250 to 600 μ m (30 to 60 mesh) screen to remove any foreign materials or undispersed pigment particles.

13.5.1.5 When materials incorporating a catalyst or converter are mixed, the addition of converter beyond that recommended by the manufacturer has an adverse effect on the coating's application, curing, and performance characteristics.

13.5.1.6 Solvent can closures should be kept tight at all times to prevent the entrance of humid air, which can lead to condensation.

13.5.1.7 Manufacturer's shelf life recommendations for structure coating components should be followed.

13.6 Application Equipment

13.6.1 Most coatings are applied by spray. Conventional spray pressure pots shall be equipped with dual regulators and an air-driven agitator. All spray equipment must be equipped with fluid tips, needles, and air caps consistent with the coating manufacturer's recommendations. The air supply line to the pressure tank must be fitted with an efficient oil and moisture separator. For applications by airless spray, a hydraulic pump that achieves a minimum pressure-compounding ratio of 30:1 should be used. An atomizing tip consistent with the manufacturer's recommendation should be selected. The tip should provide the degree of atomization and optimum fan width consistent with the configuration of the structure to be coated.

13.6.2 Clean cans and strainers should be provided for mixing the coating materials.

13.6.3 An air source that can supply a minimum of $0.85 \text{ m}^3/\text{min}$ (30 cfm) at 690 kPa (100 psig) at the nozzle for spraying operation should be available.

13.7 Typical Coating Systems in Use

13.7.1 Table 3 illustrates coating systems commonly used in the atmospheric zone of offshore structures

and associated equipment. These systems are not presented as recommendations, nor does the order listed indicate preference or superiority of one system over another. The selection of a coating system should be based on the criteria outlined in Paragraph 13.4 and/or results from field experience and maintenance programs.

Table 3: Typical Coating Systems Used in the Atmospheric Zone^(A)

	Thickn	less
Coating System	μm	mils
Inorganic zinc-rich self-cured primer	75	3
Epoxy tie-coat	50	2
High-build polyurethane	150 to 200	6 to 8
Epoxy intermediate and topcoat (2 coats)	250	10
Vinyl high-build intermediate coat	100 to 150	4 to 6
Vinyl topcoat (2 coats)	50	2
Epoxy intermediate coat	100 to 150	4 to 6
Vinyl acrylic or polyurethane topcoat	50	2
Co-polymer tie-coat	50	2
Vinyl high-build topcoat	150 to 250	6 to 10

^(A) The specified number of coats and the thickness may vary among operators and manufacturers

13.7.2 Maintenance coatings must be compatible with the original coating system.

13.7.3 The frequency and extent of recoating or touch-up work to be performed depends on many variables, including the following items:

(a) Extent and location of corrosion damage on the structure,

(b) Stress or loading of the affected structure members,

(c) Danger of spills and leaks from production piping and vessels,

(d) Cost of recoating work, including set-up charge,

(e) Cost of deferred production and any equipment downtime during coating operations,

- (f) Safety of personnel, and
- (g) Appearance factors.

13.8 Coatings for Production Equipment and Piping located on Structures

13.8.1 For most equipment operating at ambient temperatures, many of the systems listed in Table 3 are in widespread use. 13.8.2 Some surfaces on heaters, compressors, or other equipment may have elevated temperatures. If coatings are needed on these surfaces, special high-temperature coatings are available. Other processes, such as metalizing, porcelainizing, or using ceramic coatings, may also be considered.

13.8.3 For intricate shapes such as manifolds and christmas trees, care must be taken to avoid applying an excessively thick coating (see Paragraph 13.9.5).

13.9 Special Problems in Offshore Coating Programs

13.9.1 Thorough planning is necessary for applying coatings offshore. The problems of logistics, accessibility, scheduling, housing, and storage are more critical and far more costly than when applying coatings onshore.

13.9.2 The structure to be coated should be surveyed by representatives of the owner, supplier, and the contractor to consider the following aspects of the structure:

- (a) Accurate area measurements,
- (b) Condition of steel,
- (c) Protection of production equipment required,

NACE International

(d) Type and amount of rigging scaffolds and safety equipment required,

(e) Deck space and housing,

(f) Availability of transportation for workers, equipment, material, and supplies,

(g) Excess equipment on structures that may require moving, and

(h) Appropriateness of specified coating systems based on the exposure and logistics of the structure.

13.9.3 In scheduling and coordinating structure operation, the coating work should be given special consideration. Company personnel must be informed of the coating work to prevent salt-water washdowns and spills of oil or mud chemicals on blasted or primed surfaces. Workovers, drilling, or construction can seriously hinder or delay the coating work.

13.9.4 Company personnel and inspectors must be familiar with the problems and requirements of surface preparation and application of the coating materials.

13.9.5 In applying coating to intricate shapes or in pipe-congested areas, it is difficult to maintain thin films. Coatings such as inorganic zinc-rich primers, which are sensitive to excessive thickness and mud-

crack and spall at a thickness of about 100 μ m (4 mils) or more, must be avoided unless special care is exercised during application.

13.10 Galvanizing

13.10.1 Hot-dip galvanizing is an effective method for protecting complex steel shapes that would be costly and difficult to coat by conventional means. Such shapes as grating, handrails, stairs, meter houses, equipment skids, and others may be protected by galvanizing.

13.10.2 Galvanizing, like other zinc coatings, is subject to attack by acid and alkaline conditions, and should not be exposed to cement, drilling mud, or well acid.

13.10.3 Because galvanized coatings sacrifice themselves galvanically when exposed in the splash zone or when immersed, causing rapid breakdown or failure, other materials or overcoating should be used instead.

13.10.4 Galvanized metal can be overcoated by the use of suitable primers and topcoats for better chemical and salt-water exposure.

13.10.5 All galvanizing shall be applied in accordance with ASTM A 123^{33} and A $153.^{34}$

Section 14: Coatings Inspection

14.1 Introduction

14.1.1 This section provides inspection procedures to verify compliance with the governing coating specifications.

14.1.2 The inspection tools suggested for use by the inspectors are needed to provide acceptable results. Judgment based on broad experience, however, is the best inspection tool available.

14.1.3 A pre-job conference should be held to stipulate the responsibilities and relationship of the owner, inspector, applicator, and coatings supplier.

14.2 Job Orientation

14.2.1 Inspectors should thoroughly familiarize themselves with the particular job to be done. Careful notes should be made initially so that confusion is eliminated later. Acknowledgement of receipt of project specification, and understanding of same, should be made.

14.2.2 Inspectors should acquaint themselves with the materials to be used on the job.

14.2.2.1 The specification should state abrasive requirements and anchor pattern according to standards on which a mutual agreement has been reached.

14.2.2.2 All coating materials should be checked at the job site for conformance to specifications. Prior to the initiation of the job, the inspector should be provided the applicable product technical and material safety information; such information shall be made readily available by the coatings supplier. Incompatibilities should be reported prior to initiation of the job.

14.2.3 The inspector should make an initial inspection of all equipment on the job site to ensure and document that it meets the job requirements.

14.2.3.1 Special attention should be paid to abrasive-blasting equipment. The inspector should verify and enforce the specifications for abrasiveblast equipment to ensure that the compressors are sized properly for the number of nozzles and hoses, and that gaskets and nozzles are properly sized and in good condition. Air quality should be checked for cleanliness and dryness (see Paragraph 12.5.1.3). Documentation of verifications should be made.

14.2.3.2 The inspector should routinely inspect painting equipment to see that it is in good condition and meets manufacturer's specifications for the materials to be applied. Documentation of verifications should be made.

14.2.3.3 Rigging and special scaffolding equipment should be checked for safety and adequacy for the job and compliance with the owner's and applicable regulatory requirements.

14.2.3.4 The inspector should inspect all surfaces blasted to ensure that they meet specifications prior to any coating application.

14.3 Coating Application

14.3.1 The inspector should not allow coating application when the steel temperature is within $3^{\circ}C$ ($5^{\circ}F$) of the dew point.

14.3.2 The inspector should check the application equipment to ensure that proper pressures are being used for the materials specified.

14.3.3 The inspector should check each applicator to ensure that proper techniques are being used. Unsafe practices should be reported.

14.3.4 The inspector should ensure that materials sequence specifications are being followed.

14.3.4.1 The dry film thickness (DFT) of each coat should be checked to ensure that thickness specifications are met.

14.3.4.2 The cure or drying time should be checked to ensure that specifications are followed.

14.3.5 The final surface can be checked for holidays on nonconducting films.

14.3.6 The inspector should approve or disapprove all surfaces prior to beginning the next coating operation. Surfaces not meeting specifications should be redone.

14.3.7 The inspector should ensure that all surfaces to be coated are free of oil, grease, salt deposits, and moisture.

14.4 Inspection Equipment

14.4.1 The nozzle orifice gauge is required for measuring wear on abrasive-blast nozzles.

14.4.2 The nozzle pressure gauge is required to measure actual pressure at the nozzle.

14.4.3 A surface profile comparator can be used to determine surface profile or anchor pattern. Replica tapes as described in NACE Standard RP0287³⁵ can also be used to measure the anchor pattern.

14.4.4 A set of NACE surface preparation standards for comparing surface preparation is recommended (see Paragraph 12.3).

14.4.5 A humidity gauge or sling psychrometer should be used to measure humidity and temperature.

14.4.6 A wet-film thickness gauge should be used.

14.4.7 Dry-film thickness (DFT) should be measured with a nondestructive magnetic-type dry-film thickness gauge.

14.4.8 A wet sponge-type holiday detector can be used on nonconducting coatings for detecting holidays. A high-voltage holiday detector is an alternative for high-build coatings (DFT >1 mm [40 mils]).

14.4.9 A pocket knife or Tooke gauge may be used to check interfilm adhesion and hardness and to determine whether all coats of a multicoat system were applied. This is a destructive test and should be employed as a last resort.

14.4.10 A variable-width cross-hatch knife blade guide can be useful for conducting the adhesion test described in Paragraph 14.4.9.

14.4.11 Other inspection equipment might include mirrors, solvents, sample containers, adhesive tape, thermometers, and a surface roughness gauge.

14.5 Job Evaluation and Records

14.5.1 The inspector should keep a daily record that includes all phases of the work.

14.5.1.1 The notes should record the number of men working, equipment used, hours worked, and weather conditions.

14.5.1.2 A record of all materials used during any day should be made. This should include abrasives, coatings, solvents, and other materials.

14.5.1.3 Appropriate records indicating the degree of compliance to the coating specification should be completed by the inspector.

14.5.1.4 Records of type and location of coating repairs should be kept.

14.5.2 The inspector should note job progress.

14.5.2.1 The inspector should note job progress of each individual in m^2 (ft^2) per day.

14.5.2.2 The inspector should note total job progress of the entire crew per day and record as total m^2 (ft^2) per day.

14.5.3 The job may be evaluated using data from Par-

agraphs 14.5.1 through 14.5.2.2 as measures of crew efficiency and cost per m^2 (ft^2).

14.5.4 Complete records should be kept so that coating systems can be evaluated on the basis of cost per m^2 (ft²) per year.

Section 15: Corrosion Control Records

15.1 Introduction

15.1.1 This section describes a system of corrosion control records for documenting data pertinent to the design, installation, operation, maintenance, and effect-tiveness of the CP and coating systems.

15.1.2 Included in this section is an exhaustive listing of possible records. Each operator should decide on the records that are necessary for control of corrosion on the structure.

15.1.3 Information regarding the location of anodes, electrical leads, and rectifiers can be conveniently recorded on a drawing of the structure being protected. More of the potential survey data and results of maintenance inspections can be maintained in tabular form and kept up-to-date with periodic entries.

15.1.4 As-built drawings should reflect any changes from design specifications, particularly deviation in setting depth, which would alter the interval covered by the splash zone. Deviation in setting depth may occur through errors in water depth estimate (initial survey) or through settlement of the structure (possible over field life).

15.2 CP Systems

15.2.1 Galvanic (sacrificial) anode system—The following should be recorded:

15.2.1.1 Design criteria used: design life, assumed anode output and consumption rate, and current density requirements.

15.2.1.2 Number, size, composition, and (if known) the manufacturer, cost, and supplier of the anodes.

15.2.1.3 Location of each anode, the method of attachment, and date of installation. If anodes are installed during structure construction, the date of actual setting of the structure offshore should be recorded.

15.2.1.4 Number and location of anodes if checked either during construction or after setting on location, with all discrepancies noted.

15.2.2 Impressed current system—The following should be recorded:

15.2.2.1 Design criteria used (see Paragraph 15.2.1.1).

15.2.2.2 Number, size, composition, and (if known) the cost, manufacturer, and supplier of the anodes.

15.2.2.3 Location of each anode, method of attachment, and date of installation.

15.2.2.4 Specifications of the direct-current source.

15.2.2.5 Composition and location of any dielectric shielding used.

15.2.2.6 Current and voltage output of each rectifier as called for in Paragraphs 9.3 and 9.5, noting any adjustments made.

15.2.3 Combination system

15.2.3.1 A combination system is one containing galvanic (sacrificial) anodes in addition to an impressed current system.

15.2.3.2 Records for a combination system must include complete information for each of the component systems.

15.2.4 Structure potential measurements

15.2.4.1 Each time the potential of the structure is measured, the type of reference cell and the measuring technique (diver-held, guided, permanent, or freely suspended) used should be recorded.

15.2.4.2 The structure potential should be recorded initially and at the time intervals specified in Paragraph 9.4.

15.2.5 Operation and inspection—The following should be recorded:

15.2.5.1 Results of underwater inspection of the anode system, noting all discrepancies such as missing anodes.

15.2.5.2 Location, size, and type of corrosion damage found during any underwater inspection, and location and general description of trash metal located on and around the base of the structure.

15.2.5.3 Size, composition, location, number, method of attachment, cost, supplier, and date of installation of all replacement anodes.

15.2.5.4 Any maintenance performed on the rectifier.

15.2.5.5 Downtime of the impressed current system, whenever possible.

15.2.5.6 Any enlargement of the structure or addition of pipelines and flowlines. Any deviation in setting depth (see Paragraph 15.1.4).

15.3 Coating and Cladding Systems

15.3.1 This section pertains to the coatings used in atmospheric and submerged zones and the special coatings and claddings, both metallic and nonmetallic, used in the splash zone.

15.3.2 When wear plates are specified for the splash zone, the anticipated corrosion rate assumed in the design calculations should be recorded.

15.3.3 Initial installation—The following should be recorded:

15.3.3.1 Surface preparation, primer, intermediate, and topcoats used, including the quality of surface preparation, the DFT of each coat, and the number of coats.

15.3.3.2 Coating manufacturer(s), applicator, and date of application.

15.3.3.3 Inspection procedure and the results of any spot tests for film thickness and holidays.

15.3.3.4 Cost of surface preparation, coating material, and coating application.

15.3.4 Inspection

15.3.4.1 Coating and cladding systems should be inspected on a regular basis.

15.3.4.2 Location, type, and amount of deterioration found should be recorded during each inspection.

15.3.5 Maintenance—The following should be recorded:

15.3.5.1 Date of each touch-up and recoating job and the reason for the job, such as post-erection, post-drilling, routine maintenance, etc.

15.3.5.2 Total area recoated, the surface preparation and coating system used, and the inspection procedure.

15.3.5.3 Name of the coating contractor, labor materials, and equipment used, and the total cost of the job.

References

1. NACE Standard RP0169 (latest revision), "Control of External Corrosion on Underground or Submerged Metallic Piping Systems" (Houston, TX: NACE).

2. R. Baboian, ed., NACE Corrosion Engineer's Reference Book, 3rd ed. (Houston, TX: NACE, 2002).

3. NACE International 2002 Glossary of Corrosion-Related Terms (Houston, TX: NACE, 2002).

4. API RP 2A-WSD (latest revision), "Planning, Designing, and Constructing Fixed Offshore Platforms—Working Stress Design" (Washington, DC: API).

5. API RP 2A-LRFD (latest revision), "Recommended Practice for Planning, Designing, and Constructing Fixed Offshore Platforms—Load and Resistance Factor Design" (Washington, DC: API).

6. M.G. Fontana, Corrosion Engineering, 3rd ed. (New York, NY: McGraw Hill, 1986).

7. ASTM B 418 (latest revision), "Standard Specification for Cast and Wrought Galvanic Zinc Anodes" (West Conshohocken, PA: ASTM).

8. MIL-A-18001 (latest revision), "Anodes, Sacrificial Zinc Alloy" (Washington, DC: Government Printing Office).

9. "Tests Indicate the Ag/AgCl Elec Is Ideal Reference Cell in Sea Water," Materials Protection and Performance 11, 5 (May 1972): pp. 19-22.

10. W.H. Hartt, E. Lemieux, "A Principal Determinant in Cathodic Protection Design of Offshore Structures—The Mean Current Density," Corrosion 56, 10 (2000): pp. 988-997.

11. NACE Standard RP0387 (latest revision), "Metallurgical and Inspection Requirements for Cast Sacrificial Anodes for Offshore Applications" (Houston, TX: NACE).

NACE International

12. MIL-STD-2138 (latest revision), "Metal Sprayed Coatings for Corrosion Protection Aboard Naval Ships," November 23, 1981.

13. ASTM C 633 (latest revision), "Standard Test Method for Adhesion or Cohesion Strength of Thermal Spray Coatings" (West Conshohocken, PA: ASTM).

14. SSPC-SP 1 (latest revision), "Solvent Cleaning" (Pittsburgh, PA: SSPC).

15. NACE No. 1/SSPC-SP 5, "White Metal Blast Cleaning" (Houston, TX: NACE, and Pittsburgh, PA: SSPC).

16. NACE No. 2/SSPC-SP 10, "Near-White Metal Blast Cleaning" (Houston, TX: NACE, and Pittsburgh, PA: SSPC).

17. NACE No. 3/SSPC-SP 6, "Commercial Blast Cleaning" (Houston, TX: NACE, and Pittsburgh, PA: SSPC).

18. NACE No. 4/SSPC-SP 7, "Brush-Off Blast Cleaning" (Houston, TX: NACE, and Pittsburgh, PA: SSPC).

19. ISO 8501-1 (latest revision), "Preparation of steel substrates before application of paints and related products— Visual assessment of surface cleanliness—Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings" (Geneva, Switzerland: ISO).

20. Good Painting Practice, SSPC Painting Manual, Vol. 1, 4th ed. (Pittsburgh, PA: SSPC).

21. ASTM D 4285 (latest revision), "Standard Test Method for Indicating Oil or Water in Compressed Air" (West Conshohocken, PA: ASTM).

22. ASTM B 117 (latest revision), "Standard Practice for Operating Salt Spray (Fog) Apparatus" (West Conshohocken, PA: ASTM).

23. ASTM G 152 (latest revision), "Standard Practice for Operating Open Flame Carbon Arc Light Apparatus for Exposure of Nonmetallic Materials" (West Conshohocken, PA: ASTM).

24. ASTM G 153 (latest revision), "Standard Practice for Operating Enclosed Carbon Arc Light Apparatus for Exposure of Nonmetallic Materials" (West Conshohocken, PA: ASTM).

25. ASTM G 154 (latest revision), "Standard Practice for Operating Fluorescent Light Apparatus for UV Exposure of Nonmetallic Materials" (West Conshohocken, PA: ASTM).

26. ASTM G 155 (latest revision), "Standard Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials" (West Conshohocken, PA: ASTM).

27. ASTM D 2247 (latest revision), "Standard Practice for Testing Water Resistance of Coatings in 100% Relative Humidity" (West Conshohocken, PA: ASTM).

28. ASTM D 522 (latest revision), "Standard Test Methods for Mandrel Bend Test of Attached Organic Coatings" (West Conshohocken, PA: ASTM).

29. ASTM D 968 (latest revision), "Standard Test Methods for Abrasion Resistance of Organic Coatings by Falling Abrasive" (West Conshohocken, PA: ASTM).

30. ASTM D 3359 (latest revision), "Standard Test Methods for Measuring Adhesion by Tape Test" (West Conshohocken, PA: ASTM).

31. ASTM D 3363 (latest revision), "Standard Test Method for Film Hardness by Pencil Test" (West Conshohocken, PA: ASTM).

32. ASTM D 4214 (latest revision), "Standard Test Methods for Evaluating the Degree of Chalking of Exterior Paint Films" (West Conshohocken, PA: ASTM).

33. ASTM A 123 (latest revision), "Standard Specification for Zinc (Hot-Dip Galvanized) Coatings on Iron and Steel Products" (West Conshohocken, PA: ASTM).

34. ASTM A 153 (latest revision), "Standard Specification for Zinc Coating (Hot-Dip) on Iron and Steel Hardware" (West Conshohocken, PA: ASTM).

35. NACE Standard RP0287 (latest revision), "Field Measurement of Surface Profile of Abrasive Blast Cleaned Steel Surfaces Using a Replica Tape" (Houston, TX: NACE).

36. I. Rippon, "Platform Cathodic Protection Design in the South China Sea," CORROSION/97, paper no. 475 (Houston, TX: NACE, 1997).

37. R.W. Revie, ed., Uhlig's Corrosion Handbook (Indianapolis, IN: John Wiley & Sons Inc.⁽¹¹⁾ 1985).

38. Navy Ships Technical Manual, Chapter 9920, Welding and Allied Processes, NAVSHIPS⁽¹²⁾ 0901-920-0003, August 1971. (No longer in print.)

⁽¹¹⁾ John Wiley & Sons Inc., 111 River Street, Hoboken, NJ 07030.

⁽¹²⁾ Naval Sea Systems Command, 1333 Isaac Hull Avenue S.E., Washington Navy Yard, DC 20376.

39. H.B. Dwight, "Calculations of Resistance to Ground," Electrical Engineering 55, 12 (1936): pp. 1319-1328.

40. J.E. McCoy, "Corrosion Control by Cathodic Protection," in Transactions of the Institute of Marine

Engineering,⁽¹³⁾ volume 82 (London, UK: IMarEST, 1970), pp. 82-86.

41. NACE Publication 7L198 (latest revision), "Design of Galvanic Anode Cathodic Protection Systems for Offshore Structures" (Houston, TX: NACE).

Bibliography

- Anthony D.R. "Unique Methods for Applying and Monitoring Platform Cathodic Protection in Cook Inlet, Alaska." *Materials Performance* 13, 8 (1974): pp. 9-16.
- Baboian, R. "Platinum Consumption in Cathodic Protection Anodes." *MP* 16, 3 (1977): pp. 20-22.
- Benedict, R.L., ed. Anode Resistance Fundamentals and Applications—Classic Papers and Reviews. Houston, TX: NACE, 1986.
- Bone, L. "Method for Accelerated Testing of Atmospheric Coatings for Offshore Structures." CORROSION/89, paper no. 217. Houston, TX: NACE, 1989.
- Burgbacher, J.A. "Cathodic Protection of Offshore Structures." *Materials Protection* 7, 4 (1968).
- Chen, S., and W.H. Hartt. "Path Dependence of the Potential-Current Density State for Cathodically Polarized Steel in Sea Water." CORROSION/96, paper no. 553. Houston, TX: NACE, 1996.
- Cochran, J.C. "Modified Dwight, McCoy, Modified Peterson and Sunde Anode to Electrolyte Resistance Equations and Their Correlation." CORRINTEC/USA, 1981.
- Coke, J.R. "Protective Coatings for Offshore Equipment and Structures." *MP* 29, 5 (1990): pp. 35-38.
- Collected Papers on Cathodic Protection Current Distribution. Houston, TX: NACE, 1989.
- Conlin, T. "Fundamentals of Offshore Coating Operations." JPCL 7, 9 (1990): pp. 36-47.
- Crennell, J.T., and W.C.G. Wheeler. "Zinc Anodes in Seawater." *Journal of Applied Chemistry* 6, 10 (1956): p. 415.
- Davis, J.G., G.L. Doremus, and F.W. Graham. "The Influence of Environment on Corrosion and Cathodic Protection." *Journal of Petroleum Technology* 3 (1972): pp. 323-328.

- Designing Impressed Current Cathodic Protection Systems With Durco Anodes, 2nd ed. Dayton, Ohio: The Duriron Company, Inc., 1970.
- Doremus, G.L., and J.G. Davis. "Marine Anodes—The Old and New." *Materials Protection* 6, 1 (1967): pp. 30-39.
- Eliassen, S., and G. Valland. "Design Rules for Offshore Cathodic Protection Systems." Trans Institute of Marine Engineers, NSC Conference, 91 (1979).
- Evans, S. "Deepwater Platform Protection Using Coatings Combined with Cathodic Protection." CORRO-SION/90, paper no. 372. Houston, TX: NACE, 1990.
- Evans, S. "Use of Initial Current Density in Cathodic Protection Design." CORROSION/87, paper no. 58. Houston, TX: NACE, 1987.
- Geld, I., M.A. Acampora, W.L. Miller. "Dielectric Shields for Cathodic Protection Applications." *Materials Protection* 8, 8 (1969): pp. 23-24.
- Grosz, O.L. "Evaluation of Corrosion Damage Due to Improper Grounding of Welding Unit on Offshore Platforms (Stray Currents)." CORROSION/76, paper no. 179. Houston, TX: NACE, 1976.
- Hanson, H.R., and D.C. Hurst. "Corrosion Control-Offshore Platforms." *Journal of Metals* 4 (1970): pp. 46-50.
- Hartt, W.H., and S. Chen. "Critical Considerations and Questions Pertaining to Cathodic Protection System Retrofits." CORROSION/95, paper no. 316. Houston, TX: NACE, 1995.
- Hudgins Jr., C.M., B.M. Casad, R.L. Schroeder, and C.C. Patton. "The Effect of Cathodic Protection on the Corrosion Fatigue Behavior of Carbon Steel in Synthetic Seawater." *Journal of Petroleum Technology* 3 (1971): p. 283.
- Lennox, T.J., Jr., R.E. Groover, and M.H. Peterson. "Electrochemical Characteristics of Six Aluminum Galvanic Anodes in the Sea." *Materials Protection and Performance* 10, 9 (1971): pp. 39-44.

⁽¹³⁾ The Institute of Marine Engineering, Science and Technology, 80 Coleman Street, London EC2R 5BJ, England.

- Lye, R.E. "Cathodic Protection and Coating—Design and Performance of a Corrosion Protection System for a North Sea Jacket." CORROSION/89, paper no. 282. Houston, TX: NACE, 1989.
- McCrory, E.D. "Maintenance of Protective Coating Systems on Offshore Platforms." *JPCL* 3, 4 (1986): pp. 26-31.
- Morgan, J.H. *Cathodic Protection.* Houston, TX: NACE, 1987.
- Peabody, A.W. "Sound Applications for Zinc Anodes." St. Louis, MO: American Zinc Institute, 1954.
- "Platinized Titanium Anodes for Cathodic Protection." *Technical Bulletin*. East Newark, NJ: Engelhard Industries, Inc., 1966.
- Rau, J.F., T.W. Michie, and S.N. Smith. "Cathodic Protection of Guyed Tower in 1,000 ft of Water." CORRO-SION/87, paper no. 76. Houston, TX: NACE, 1987.
- Reding, J.T., and T.D. Boyce. "Cathodic Protection Performance of Offshore Anodes at a Simulated Depth of 650 Feet." *MP* 13, 9 (1974): pp. 37-40.
- Rosbrook, R., W.H. Thomason, and J.D. Byrd. "Flame Sprayed Aluminum Coatings on Subsea Components." *MP* 28, 9 (1989): pp. 34-38.
- Schrieber, C.F., and J.T. Reding. "Field Testing a New Aluminum Anode." *Materials Protection* 6, 5 (1967): pp. 33-36.
- Smith, S.N., C.F. Schrieber, and R.L. Riley Jr. "Supplemental Studies of the Galvalum III Anode—Exposure Time and Low Temperature." CORROSION/77, paper no. 35. Houston, TX: NACE, 1977.

- Smith, S.N, J.T Reding, and R.L. Riley Jr. "Development of a Broad Application Saline Water Aluminum Anode— Galvalum III." *MP* 17, 3 (1978): pp 32-36.
- Stauffer, D.B. "Structural Design for Offshore Engineering." Australian Corrosion Engineering (June 1959): p. 3.
- Sverdrup, H.V., M.W. Johnson, and R.H. Fleming. *The Oceans*. New York, NY: Prentice-Hall, 1952.
- Szoklik, A. "Maintaining Protective Coatings on Offshore Platforms." *JPCL* 5, 5 (1983): pp. 32-40.
- Szoklik, A. "Splash Zone Protection: A Review of 20 Years in the Bass Strait." *JPCL* 6, 12 (1989): pp. 46-55.
- Thomason, W.H. "Offshore Corrosion Protection with Thermal-Sprayed Aluminum." Proceedings of the 17th Annual Offshore Technology Conference, paper no. 4971 (1985).
- Thomason, W.H., S.E. Pape, and S. Evans. "The Use of Coatings to Supplement Cathodic Protection of Offshore Structures." *MP* 26, 11 (1987): pp. 22-27.
- Townley, D.W. "Unified Design Equation for Offshore Cathodic Protection." CORROSION/97, paper no. 473. Houston, TX: NACE, 1997.
- Uhlig, H.H. *Corrosion Handbook.* New York, NY: John Wiley and Sons, Inc., 1948.
- Vennett, R.M., and R.R. Matthews. "Stratification of Water Properties Along the Louisiana Coast and Its Influence on Cathodic Protection Systems." MP 14, 7 (1975): pp. 31-39.
- Wang, W., and W.H. Hartt. "Experimental Protocol and Data Representation for Sacrificial Anode Cathodic Protection of Steel in Seawater." CORROSION/93, paper no. 520. Houston, TX: NACE, 1993.

Appendix A: Typical Design Parameters for Offshore Petroleum Production

Structures in Selected Oil Provinces

The principal factor governing the minimum design current density at which polarization necessary for complete CP can be achieved in the open sea is the availability of corrosive (depolarizing) agents, principally oxygen, at the submerged structure surfaces. Lowering the water temperature increases both the water resistivity and oxygen solubility. Water turbulence, along with natural lateral flow, also maximizes the rate at which oxygen reaches the structure surfaces. Cook Inlet waters represent an environmental extreme; most of the above negative factors are present, in addition to scouring (mechanical depolarization) by suspended glacial silt in the swiftly flowing water. The formation of a calcareous deposit also affects the current requirement by reducing the ability of oxygen to reach the metal surface. The calcareous deposit precipitates from seawater because of the alkaline shift in pH that results from the polarization of the metal surface. Because the beneficial qualities of the calcareous deposit are reduced by decreasing water temperature and lower current densities, a relatively high initial current provision for CP can reduce the long-term current demand to maintain protection.

Laboratory and field tests have shown that rapid polarization of a steel cathode upon immersion to potentials of -0.9 to -1.0 V (Ag/AgCl [sw]) generates a more protective calcareous deposit than is achieved by slower polarization. High current densities are required to achieve these results, but current demand decreases (by as much as a factor of 10) quickly as the protective calcareous deposit is formed. At the launch of a structure the potential difference between the sacrificial anode system and the unpolarized steel may be around 0.45 V, which enables the sacrificial system to generate a very high current density on the cathode. After polarization, this potential difference decreases to 0.25 V or less with an accompanying decrease in current density.

This polarization process normally results in a linear relationship between steel potential and current density, the slope of the line being equal to the overall circuit resistance of the CP system, or the design slope. For any given location, galvanic anode designs with similar design slope values result in similar long-term current densities. The relationship between design slope and maintenance current density can be established by on-site experiments or by review of experience at that location.

Current density is strongly dependent on water temperature. For deep-water structures different design values should be used for different temperature zones. To optimize the design the structure should be spilt up into separate zones over which the temperature does not vary by more than 5° C (9°F). The depth average temperature of each interval should be used to assess the required current densities.³⁶ The same approach can apply to resistivity assessment.

Table A1 presents a general guide to the design of CP systems in eleven major offshore petroleum producing areas. These data may be used as a starting point for investigation prior to selection of final design parameters for a specific application. Table A1 also presents equivalent design values for the same producing areas.

Figure A1 represents the temperature curves based on current density.

Table A1: Design Criteria For Cathodic Protection Systems

Production Area	Water Resistivity ^(B)	Water Temp. (°C)	Environmental Factors ^(A)		nmental tors ^(A) Typical Design Current Density ^(C) mA/m ² (mA/ft ²)		urrent	Typical Design Slope
			Turbulence L Factor V (Wave Action)	Turbulence Factor	e Lateral Water Flow		,	
	(ohm-cm)	- F (-)		Flow		Flow	Initial ^(E)	Mean ^(F)
Gulf of Mexico	20	22	Moderate	Moderate	110 (10)	55 (5)	75 (7)	4.1 (44)
U.S. West Coast	24	15	Moderate	Moderate	150 (14)	90 (8)	100 (9)	3.0 (32)
Cook Inlet	50	2	Low	High	430 (40)	380 (35)	380 (35)	1.0 (11)
Northern North Sea ^(D)	26 to 33	0 to 12	High	Moderate	180 (17)	90 (8)	120 (11)	2.5 (27)
Southern North Sea ^(D)	26 to 33	0 to 12	High	Moderate	150 (14)	90 (8)	100 (9)	3.0 (32)
Arabian Gulf	15	30	Moderate	Low	130 (12)	65 (6)	90 (8)	3.5 (37)
Australia	23 to 30	12 to 18	High	Moderate	130 (12)	90 (8)	90 (8)	3.5 (37)
Brazil	20	15 to 20	Moderate	High	180 (17)	65 (6)	90 (8)	2.5 (27)
West Africa	20 to 30	5 to 21	Low	Low	130 (12)	65 (6)	90 (8)	3.5 (37)
Indonesia	19	24	Moderate	Moderate	110 (10)	55 (5)	75 (7)	4.1 (44)
South China Sea	18	30	Low	Low	100 (9)	35 (3)	35 (3)	

Resistivities (ohm-cm) Temperature (°C [°F])

Chlorinity (ppt)	0 (32)	5 (41)	10 (50)	15 (59)	20 (68)	25 (77)
19	35.1	30.4	26.7	23.7	21.3	19.2
20	33.5	29.0	25.5	22.7	20.3	18.3

^(A) Typical values and ratings based on average conditions, remote from river discharge.

^(B) Water resistivities are a function of both chlorinity and temperature. In the Corrosion Handbook³⁷ by H.H. Uhlig the following resistivities are given for chlorinities of 19 and 20 parts per thousand (ppt). (^(C) In ordinary seawater, a current density less than the design value suffices to hold the structure at protective potential once polarization has been

accomplished and calcareous coatings are built up by the design current density. CAUTION: Depolarization can result from storm action.

⁹ Conditions in the North Sea can vary greatly from the northern to the southern area, from winter to summer, and during storm periods.

(E) Initial current densities are calculated using Ohm's Law and a resistance equation such as Dwight's or Crennell's (McCoy's) equation with the original dimensions of the anode. An example of this calculation is given in Appendix D, which uses an assumed cathode potential of -0.80 V (Ag/AgCl [sw]).

Mean current densities are used to calculate the total weight of anodes required to maintain the protective current to the structure over the design life. Examples of these calculations are given in Appendixes D and E. ^(G) Final current densities are calculated in a manner similar to the initial current density, except that the depleted anode dimensions are used. An

example of this calculation is given in Appendix D.



Appendix B: Energy Capabilities and Consumption Rates of Various Commercial Galvanic Anodes Available for Cathodic Protection of Offshore Structures

The energy capability of a given galvanic anode material is usually expressed in terms of ampere-hours per kg (lb) of material. This figure, when divided into the number of hours per year (8,760), gives the anode consumption rate in kg (lb) per ampere-year, a more useful form of energy rating to the design engineer.

The energy capability of any galvanic anode material selected for use in offshore CP design should be previously established through controlled laboratory and field tests at an anode current density normally expected in field applications, i.e., approximately 2.2 to 7.5 A/m^2 (200 to 700 mA/ft²) of anode surface. Table B1 lists the established energy capabilities of some of the more commonly used galvanic anode materials at anode loadings of 2.2 to 7.5 A/m² (200 to 700 mA/ft²). The differences shown for any one material are attributed to variations in composition and/or heat treat-

ment offered by the various manufacturers. Table B1 also lists the corresponding anode consumption rates, calculated as stated above. Therefore, it is prudent in design of galvanic CP systems to consider that anode capacity may be less than is predicted from short-term testing.

Segregation of some minor alloys and/or impurities during cooling can alter the galvanic properties of the anode material. Any potential segregation is more pronounced on the interior portions of larger anodes because of slower cooling after casting.

Any anode material must be capable of a sufficient driving voltage to provide the necessary design current output. A check for proper driving voltage of an anode can be made by measuring the closed-circuit potential of the anode, using a suitable reference cell.

Galvanic Anode Material	Energy Capability ^(A) A-h/kg (A-h/lb)	Consumption Rate Kg/A-yr (Ib/A-yr)	Anode to Water ^(B) Closed Circuit Potentials, Negative Volts (Ag/AgCl[sw])
Aluminum-zinc-indium	2,290 to 2,600 (1,040 to 1,180)	3.8 to 3.4 (8.4 to 7.4)	1.05 to 1.10
Aluminum-zinc-mercury	2,760 to 2,840 (1,250 to 1,290)	3.2 to 3.1 (7.0 to 6.8)	1.0 to 1.05
Aluminum-zinc-tin	930 to 2,600 (420 to 1,180)	9.5 to 3.4 (20.8 to 7.4)	1.0 to 1.05
Zinc (MIL-A-18001) ⁸	770 to 820 (350 to 370)	11.2 to 10.7 (25.0 to 23.7)	1.0 to 1.05
Magnesium (H-1 allov)	1.100 (500)	8.0 (17.5)	1.4 to 1.6

^(A) The above data show ranges that are taken from field tests at Key West, Florida, by Naval Research Laboratory, Washington, DC,³⁸ and from manufacturers' long-term field tests. Modification to these numbers will be made only by recommendation from NACE International STG 30 on Oil and Gas Production—Cathodic Protection. ^(B) Measured potentials can vary because of temperature and salinity differences.

Appendix C Consumption Rates in Seawater of Various Commercial Types of Impressed Current Anodes Available for Cathodic Protection of Offshore Structures

Impressed current anodes, unlike galvanic anodes, can be driven over a wide range of anode current densities, depending on the designer's preferences and the demands of a particular application. Because anode current loadings have a definite bearing on consumption rates, any meaningful listing of consumption rates for various anode materials must necessarily include the approximate anode current density at which such rates have been established. Table C1 lists consumption rates of various impressed current anode materials used for CP systems on offshore structures. If titanium is used as the substrate for a platinum-type anode, anode/electrolyte voltage must be limited to about 8 V. For niobium substrates, laboratory data indicate that voltages as high as 100 V are satisfactory; however, field experience shows that 50 V is a more reliable and practical limit.

Table C1: Consumption Rates of Impres	ssed Current Anode Materials
---------------------------------------	------------------------------

Impressed Current Anode Material	Typical Anode Current Density in Saltwater Service A/m ² (A/ft ²)	Nominal Consumption Rate g/A-yr (Ib/A-yr)
Pb-6%Sb-1%Ag	160 to 220 (15 to 20)	14 to 90 (0.03 to 0.2 ^(A))
Pb-6%Sb-2%Ag	160 to 220 (15 to 20)	14 to 27 (0.03 to 0.06 ^(B))
Platinum (on Titanium, Niobium, or Tantalum substrate or mixed metal oxide)	540 to 3,200 (50 to 300)	3.6 to 7.3 (0.008 to 0.016 ^(B))
Graphite	10 to 40 (1 to 4)	230 to 450 (0.5 to 1.0)
Fe-14.5%Si-4.5%Cr	10 to 40 (1 to 4)	230 to 450 (0.5 to 1.0)

^(A) Very high consumption rates of Pb-Ag anodes have been experienced at depths below 30 m (100 ft).

^(B) This figure can increase when current density is extremely high and/or in low-salinity waters.

Appendix D: Typical Method for Calculation of Galvanic Anode Current Output Using Initial, Maintenance, and Final Current Densities

This method has been commonly employed in the past for CP design, so practitioners tend to be familiar with it. The disadvantage is that it is based on an algorithm rather than being first principles-based and can lead to unnecessary over-design compared to the slope parameter method (see Appendix E). The over-design can be minimized if a range of anode sizes is considered, and the size selected on the one that gives the lowest installed cost.³⁶ From a modification of Dwight's equation,³⁹ the resistance of a cylindrically shaped anode to the electrolyte in which it is placed is equal to the product of the specific resistivity of the electrolyte and certain factors relating to the shape of the anode, as given in Equation (D1):

$$R = \rho \frac{K}{L} \left[ln \left(\frac{4L}{r} \right) \right] - 1$$
 (D1)

where:

- R = anode-to-electrolyte resistance in ohms
- ρ = resistivity of the electrolyte in ohm-cm. (See Table A1)

- K = 0.500/ $\!\pi$ or 0.159 if L and r units are in cm or 0.0627 if L and r units are in inches
- L = length of anode in centimeters
- r = radius of anode in centimeters (for other than cylindrical shapes, $r = C/2\pi$, where C = cross-section perimeter).

Thus, for a 25 x 25 cm (10 x 10 in.) cross-section, C = 100 cm (40 in.), and r = 15.9 cm (6.27 in.).

To determine the current output from an anode, use Ohm's Law: I = E/R.

For a typical calculation for an anode in the Gulf of Mexico, the number of anodes required for protection must satisfy three different calculations. There must be enough anodes to polarize the structure initially (initial current density from Table A1), to produce the appropriate number of amps of current over the design life of the structure (mean current requirement), and to produce enough current to maintain protection at the end of the design life (final current requirement). For this exercise, we are given the following information:

Structure surface area = $9,300 \text{ m}^2 (100,000 \text{ ft}^2)$

Design life = 20 years

 ρ = 20 ohm-cm (from Table A1).

Based on this information, we select an anode with the following characteristics:

Material: aluminum-zinc-mercury alloy

E = 0.25 V driving force between an aluminum or zinc anode of -1.50 V (Ag/AgCl [sw] reference).

L = 244-cm (96-in.) anode length,

r = 13.7-cm (5.40-in.) anode radius initially for a 22- x 22cm (8.5- x 8.5-in.) anode on a 10-cm (4-in.) core,

Wt = 330-kg (725-lb) weight per anode,

CC= 2,750 A-hr/kg (1,250 A-hr/lb) for current capacity for Al-Zn-Hg alloy anodes from Table B1 or anode supplier's specifications,

 $r_{core} = 5.7$ cm (2.25 in.), which is one-half the OD of an 11- cm (4-in.) Sch. 80 pipe.

Therefore, the initial current output per anode is as shown in Equation (D2):

$$I = \frac{E}{R} = \frac{0.25V}{20 \frac{0.159}{244} \left[ln \left(\frac{4 \times 244 \text{ cm}}{13.7 \text{ cm}} \right) - 1 \right]} = \frac{0.25V}{0.0426 \text{ ohm}} = 5.86A$$
(D2)

The number of anodes required to protect a structure with $9,300 \text{ m}^2$ (100,000 ft²) of exposed surface area is as shown in Equation (D3):

$$N = \frac{\text{Initial Current Density} (110 \text{ mA/m}^2) \times \text{Surface Area} (9,300 \text{ m}^2)}{\text{Amps output per anode} (5.86) \times 1,000 \text{ mA/A}} = 175 \text{ anodes}$$
(D3)

The initial current density (110 mA/m2) is obtained from Table A1.

In order to meet the second current density requirement for the structure, which determines the number of kg (lb) of anode material required to protect the structure over the 20year design life, use Equation (D4):

$$N = \frac{\text{Mean Current Density (55 mA/m2) × Surface Area (9,300 m2) × Life (20 yr) × 8.760 (hr/yr)}{(2,750 A hr/kg × 330 kg/anode × 1,000 mA/A)} = 99 \text{ anodes}$$
(D4)

`

The mean current density (55 $\mbox{mA/m}^2\mbox{)}$ is obtained from Table A1.

Lastly, the number of anodes to provide the final current requirement is calculated in a manner similar to the initial current requirement, except that the expended dimensions of the anode are used to represent the anode at the end of its life (see Equation (D5).

$$r_{\text{expended}} = r_{\text{initial}} - (r_{\text{initial}} - r_{\text{core}}) \times 0.9 = 13.7 - [(13.7 - 5.7)(0.9)] = 6.5 \text{cm}$$
(D5)

where 0.9 is the anode utilization factor for a standoff anode. Assume no change in anode length.

The final current output per anode is shown in Equation (D6):

$$I = \frac{E}{R} = \frac{0.25 \text{ V}}{20 \frac{0.159}{244} \text{ ln } \frac{4 \times 244 \text{ cm}}{6.5 \text{ cm}} - 1} = \frac{0.25 \text{ V}}{0.0523 \text{ ohm}} = 4.78 \text{ A}$$
(D6)

The number of anodes required to protect a structure with $9,300 \text{ m}^2$ (100,000 ft²) of exposed surface area is as shown in Equation (D7):

$$N = \frac{\text{Final Current Density (75 mA/m2) × Surface Area (9,300 m2)}}{\text{Amps output per anode (4.78) × 1,000 mA/A}} = 146 \text{ anodes}$$
(D7)

NACE International

The final current density (75 mA/m^2) is obtained from Table A1.

The initial current calculation required 175 anodes, the mean current density requirement required 99 anodes, and the final current calculation required 146 anodes. For this application the proper number of anodes to use would be 175 anodes. However, the difference between this value and the calculated mean current requirement of 99 anodes is significant. Another anode shape that provides less variation between the three requirement values is often more economical to install.

Dwight's equation is valid when $4L/r \ge 16$; for anodes when 4L/r < 16 or for anodes that do not approximate cylindrical shapes, equations such as Crennell's (McCoy's) (see Equation [D9]) or other versions of Dwight's may better predict the actual current output of the anodes. Theoretically, for a deep sea submerged cylindrical anode, a more nearly correct equation would be as shown in Equation (D8):

$$R = \rho \frac{K}{L} \left[ln \left(\frac{2L}{r} \right) - 1 \right]$$
 (D8)

However, the first version is more widely used in CP practice.

Notes:

(a) For practical designs and to ensure adequate current to protect the structure during the life of the anode, the length (L) and radius (r) should be selected to show the condition of the anode when it is nearly consumed. For an elongated anode, the change in length may be ignored.

(b) If the structure potential rises above the minimum protection potential of -0.80 volt (Ag/AgCl [sw]), E becomes less than 0.25 V. This decreases anode current output and increases anode life.

(c) The anode net weight must be sufficient to provide the calculated current for the design life of the system, in accordance with the actual consumption rate of the anode material selected (see Appendix B and Table B1).

(d) Crennell's (McCoy's) formula is shown in Equation $(D9)^{40}$:

$$R = \frac{0.315\rho}{\sqrt{A}}$$
(D9)

where:

R = resistance in ohms ρ = resistivity of water in ohm-cm

A = area of exposed anode in cm²

Appendix E: Typical Method for Calculation of Galvanic Anode Current Output Using Design Slope and Maintenance Current Density

This method is proposed as an alternative to calculation of the initial, mean, and final current densities (Appendix D). It affords the advantage of being first principles based such that undisclosed over-design, as may be inherent to the preceding method, may be avoided. This CP system design for the seawater-exposed sections of an uncoated structure using the design slope follows these steps⁴¹:

1. Determine the required design life for the structure, T.

2. Based on the anode material to be used and the application environment, select a value for the anode consumption rate, k (Note: a different symbol for anode consumption rate is used elsewhere).

3. Specify the water resistivity, p. For large structures that span zones of varying resistivity, separate designs may be executed for different regions of the structure.

4. Based on prior experience or on experimental data at the site of interest, select values for the design slope, S, and for the maintenance current density, i_m , which results from that design slope. Again, separate designs may be executed for different regions of the structure.

5. Determine the value of the right-hand side of Equation (E1). This value then describes the anode size and shape alternatives that may be used to achieve the selected design, as dictated by the left-hand side.

$$R_a w = i_m TkS$$
 (E1)

where:

- R_a = resistance of single anode to remote seawater (for example, Equation [D1]) in ohms
- w = weight of a single anode in kg
- i_m = maintenance current density in A/m²
- T = design life in years
- k = anode consmption rate in kg/A-yr
- S = design slope in ohm-m² (many or all of these terms are defined elsewhere)

6. Iteratively determine a suitable anode for the application:

(a) Select a candidate anode, and from its dimensions calculate its resistance, $\mathsf{R}_a,$ and its mass, w.

(b) Check whether for this anode, the left-hand side of Equation (E1) is equal to the right-hand side.

(c) If there is no match, two options exist. First the anode can be modified and steps 6a and 6b repeated to optimize the anode to meet the design criteria. (Al-though an infinite number of anodes that will satisfy Equation (E1) can be designed, there is a smaller subset that is practical to manufacture and install.) Alternatively, the selected anode may be accepted, and Equation (E1) may be rearranged, as shown in Equation (E2), to determine the actual design life that will result.

$$T = \frac{R_a w}{i_m kS}$$
(E2)

7. Once the anode has been sized, Equation (E3) can be used to calculate the surface area that each anode will protect, A1:

$$A_1 = \frac{S}{R_a}$$
(E3)

where:

 A_1 = area protected per anode in m²

8. Determine the total surface area for the structure or zone to be protected, A_{total}, and divide by the area protected by each anode to determine the number of anodes needed, as shown in Equation (E4).

$$N = \frac{A_{\text{total}}}{A_1}$$
(E4)

where:

N = total number of anodes

9. Determine whether the design slope based on final conditions (90% anode consumption) is acceptable but using the value of R_a for an expended anode. R_a of an expended anode can be calculated using the same procedure described to determine the current output of an expended anode in Equations D5 and D6. The long-term potential of the anode might be different from the value exhibited during the polarization process, so that the design line may shift up or down on the polarization graph.

If a large number of designs will be done for structures in similar conditions, steps 1 through 7 and 9 of this procedure may need to be followed only once. A standard anode that will protect a certain cathode area, A1, on each structure, is thereby defined.

If a design requires that different sizes and shapes of anodes be used because of complex structure geometry, then each anode type should be independently determined to satisfy the design equation in step 6 above. The area protected by each anode type is different.